

~~CONFIDENTIAL~~
~~SECRET~~
~~TOP SECRET~~

GEORGIA-PACIFIC

INTERDEPARTMENTAL COMMUNICATION

DATE: August 31, 1971

TO: Mr. J. B. Moss

LOCATION: Tigard

FROM: L. E. Winter

LOCATION: Acme

SUBJECT: Comparison of Seven All Purpose Compounds

PLAINTIFF'S EXHIBIT

GP-772

	GP (Gypsum)	Sterling	GP (Casein)	Gold Bond	U.S.G.	Texas	In-Tex
WC	60	60	70	72	68	60	60
PH	8.7	9.0	8.4	8.3	8.35	8.7	8.85
Bond	100%	100%	100%	30%	100%	100%	100%
Workability	Good	Fair	Good	Fair	Good	Good	Poor
Shear	OK	OK	OK	OK	OK	OK	OK
Shrinkage	Good	Good	Fair	Good	Fair	Fair	Fair
Edge Crack	Good	Good	Good	Good	Good	Fair	Good
Wedge Crack	Good	Good	Fair	Good	Poor	Very Poor	Poor
Hardness	OK	OK	OK	Soft	OK	Hard	Hard
Adhesive	Vinyl	Casein	Casein	Casein	Starch	Starch	Starch
Viscosity	440	440	580	520	460	460	460
Working Time	30 min.	20 min.	30 min.	35 min.	35 min.	30 min.	10 min.

We listed the different brands in order of quality, GP being #1 and In-Tex #7.

L. E. W.
L. E. W.

LEW/om

cc: Messrs. T. W. Richards
C. W. Lehnert
D. C. Corkill
W. N. Gettel
K. W. Brown
D. M. Watson
E. Schram

THIS COPY FOR

*I will ask Lloyd to compare these (Pico)
ready mix and include Kelly's, or is
should we have him compare these, or is
this too difficult at the plant?*
Ally

SGP 0015862