

Duramix Quick Drying Enamel
Interior Trim Enamel
White
S.G.W.
Second

Actual
3/31/42

Pigment							
481-3	Lithopone	900	25.200	3.95	35.55	4.40	39.60
2030	Titanium Oxide	900	27.810	14.87	133.84	14.80	133.20
Vehicle							
(5091)	Bleached Linseed Oil	276	36.797	11.38	31.41	13.62	37.69
X-70876	Resin Mng. Varnish	1080	137.376	4.34	46.87	4.62	49.90
(348)	Mineral Spirits	432	64.498	1.55	6.70	1.50	6.48
FW(277)	Heavy Bod Lins. Oil	294	36.074	16.56	48.69	16.56	48.69
(851)	Mixing Varnish	1992	279.079	11.41	227.29	12.80	254.98
(2241)	Drier	90	12.981	10.84	9.75	11.14	10.03
(152)	Drier	14	1.921	13.65	1.91	14.32	2.00
(1767)	Anti-Skinning Agent	36	5.332	5.79	2.08	5.74	2.07
					544.10		584.54

6014 625.048 90.61 97.34

625.048
4.08%
600.50 Gals.

Net Weight
Gross Weight
Factory Overhead
Back of the line
State and local taxes
1.163 1.2

Shipped to
Under 500
OVER 500
UNDER 500
C.L.
1.97
1.68
1.97
L.C.L.
2.07
1.76
3.25
2.07
2.19

OPA ■■000754

N 4762