MO-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Rf-695-U LOT 34553

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	10	1365	24-18	

LW1364 STUMP

TOTAL NET WT. 1365 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	3/5/80	14

CG 36 CODE RT-695-D PKG.

→ FEB 27 39513

EST. WGT. 1350 LBS.

32/107

298

PROCESSING INSTRUCTIONS: BATCH UNIT

32/107

PROCESSES	APPROVED BY
RT-695-D (M)	DCG 1-12
	IHD 2425
TYPED BY	
LG 5-15-72	

Retyped 2-27-80 MnM

MAKING NOTES

REMARKS

NAME: BON RED DARK

NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	107					STARTED	1 AM				
DATE	2-28					CAKES USED	30				
TIME	1100P					WATER ON	5 PM				
RELEASED BY	JDL					HRS. WASHED	16				
PRESS	32	33	35	38	39	OHMS	40K				
NO. OF CAKES	30	60	60	60	60	HRS. WASHED					
PRESS Without		AGITATION				OHMS					
WASH TO 4000		OHMS with 35-75F water				HRS. WASHED					
REST AFTER 16		HOURS				OHMS					
LOAD on 8 cars						CAKE CONDITION	4				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

AC

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

HOURS Dry 30 hours at L.V. H.V.

TEMP. 180 °F °F

SE 15-30

Mn Color

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED 7 LUMP WGT. 1364

SAMPLED BY RELEASED BY

-GRINDING-

MILL 5 HSP 1/8" RP SCREEN 4600 RPM

MAX. TEMP. °F

Mn Color

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

999 %

SAMPLE AFTER / WITHOUT MIXING

SAMPLES Env & 2 pt cans

DELIVER TO CTL

DATE MIXED OXYGEN

SAMPLED BY 299 3/4/80 RELEASED BY

DUP050292587

N 31865.01

CG 36 CODE RT-695-D PKG. ____

FEB28 34553

EST. WGT. 1350 LBS.

PROCESSING INSTRUCTIONS: BATCH UN

	PROCESSES	APPROVED
	RT-695-D (M)	DCG 1-12
		IHD 2-25
	TYPED BY	
	LG 5-15-72	

MAKING NOTES

REMARKS

NAME: BON RED DARK

NON-BLEEDING

INSTRUCTIONS						-PRESSING- RECORD					
AT						PRESSLOAD	1ST	2ND	3RD	4TH	5T
ATE						STARTED					
IME						CAKES USED					
ELEASED BY						WATER ON					
RESS	32	33	35	38	39	HRS. WASHED					
O. OF CAKES	60	60	60	60	60	OHMS					
RESS without AGITATION						HRS. WASHED					
ASH TO 4000 OHMS with 35-75F water						OHMS					
EST AFTER 16 HOURS						HRS. WASHED					
OAD on 8 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					
AMPLES											
ELIVER TO						SAMPLED BY		RELEASED BY			

-DRYING-

Dry 24 Hours at 180F	LUMP: - OK - WET - SALTS - CONTAMINAT
SE 15-30	
Mn Color	
	ADDITIONAL DRYING HOURS REQUIRED
AMPLES	NO. CARS PULLED LUMP WGT.
ELIVER TO	SAMPLED BY RELEASED BY

-GRINDING-

ILL 5 HSP 1/8" RP SCREEN 4600 RPM	SCREEN RPM
°F	MAX. TEMP. °F
Mn Color	
	EXPLAIN LOSSES
AMPLE WITHOUT MIXING	DATE MIXED
AMPLES 1 Env & 2 pt cans	
ELIVER TO C T L	SAMPLED BY RELEASED BY

DUP050292588

N 31865.02



DUP050292589

N 31865.03