

INSULATION BLOCK

November 19, 1964

Product 60R

	Batch Weight
4.6% Amosite	12#
34.4% Vermiculite	90#
15.2% Hyflo Earth	40#
45.8% Incor Cement	120#
	262#

PLAINTIFF'S
EXHIBIT

CE-7A

#19 INSULATION BLOCK

Product 601

#12 INSULATING BLOCK

#600

January 18, 1964

	Batch Weight
43.2% PA-130 Perlite	70#
21.6% Raw Earth	35#
6.2% Amosite Fiber	10#
29.0% Incor	47#
	162#

#12 INSULATING BLOCK

#600