

**PLAINTIFF'S
EXHIBIT**

CE-7C

MIX A - A-1088

Product 703

March 22, 1965

Batch Weight

84.0% "G" Wool

420

6.0% 7-M Fiber *Asbestos*

30

6.0% Raw Earth

30

5.0% Bentonite

25

40# Bags

MIX A

Product 703

SUPER FINISH A-1362-7

PRODUCT 720

BATCH WEIGHT

Fly Ash

90 lbs

Asbestos 7-M Fiber

113.5 lbs

Raw Earth C-300

50 lbs

Bentonite Hi Yield 200 mesh

200 lbs

Wool, Fine 1/8"

220 lbs

Incor Cement

120 lbs

Sodium Nitrite

4 lbs

Orvus AB

2.5 lbs

SUPER FINISH A-1362-7

PRODUCT 720

SPECIAL STICTITE A-1236

PRODUCT 711

RE 1-4-68

BATCH WEIGHT

32.4% "G" Wool

140

32.4% Fine Wool

140

23.2% Bentonite

100

6.0% 7 M Asbestos

26

6.0% C-300 Earth

26

432

SPECIAL STICTITE A-1236

PRODUCT 711