MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky. 907 LOT 34286

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	68	3,400		
	STUMP			

TOTAL NET WT. 3400 PKG. N–CODE 1139

PROD. SPVR. [signature] DATE 2/11/80 WHSE. OPER.

N 2635

95/262

CG 03 CODE KY-907-D PKG. ____

→ FEB-7 34286

EST. WGT. 1080 LBS.

OK/R

PROCESSING INSTRUCTIONS - BATCH UNIT

PROCESSES	APPROVED BY
KY-907-D (E)	EWK 12/12/77
Alternate	DCG 12/14/77
TYPED BY	
rj 3/1/78	

MAKING NOTES

REMARKS

Total Wgt. 3480#

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

VAT					262	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE					2-9	STARTED	8:45 PM				
TIME					7:30 P	CAKES USED	40				
RELEASED BY					237	WATER ON	12M				
PRESS	2	22	23	24	95	HRS. WASHED	6				
NO. OF CAKES	46	46	46	52	4042	OHMS	2000				

PRESS with AGITATION

WASH TO 2000 OHMS with 135-145°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

HRS. WASHED

OHMS

HRS. WASHED

OHMS

CAKE CONDITION

NO. CARS LOADED 5

EXPLAIN LOSSES

D.R.

SAMPLES 8oz Jar

DELIVER TO CTL for color

SAMPLED BY 472 RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F

Dry at first stage only.
Reset every 5 hours til dry.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES

NO. CARS PULLED

LUMP WGT. 3426

DELIVER TO

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 939 HSP ~~1/8"~~ 3/32 RP SCREEN 3500 RPM

MAX. TEMP. 170 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT can

DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093975

N 26352.01

34286
41
18

0.00	*
3.12	+
0.14	-
3.06	+
0.14	-
3.04	+
0.14	-
3.22	+
0.14	-
3.16	+
0.14	-
3.10	+
0.14	-
3.21	+
0.14	-
3.01	+
0.14	-
3.10	+
0.14	-
2.91	+
0.14	-
2.98	+
0.14	-
2.03	+
0.14	-
34.26	*

DUP050093976