

PROCESS INSTRUCTIONS FOR

E.p. 3408A/Non-boiling PROFAX for one-
piece units only.

Form: one-piece top

Color of End Product: _____

Weight per Gallon: _____

Bulk Density: .70 to .80 g/cc

MIXING INSTRUCTIONS:

1. Pulp all ingredients except 265A, X-1790 and X-1791 at the 160 gallon level for 15 minutes.
2. Stop pulper and add 265A, X-1790 and X-1791 while bringing up water level to the 250 gallon level. Pulp for 1 minute only then bring up water level to 400 gallon mark.
3. Pump over to holding tank.

DATE 8/18/69

APPROVED _____

PLS 3408 2H 708

EJG

FOS-00-000002365

0717

