MCS 1043

TYPICAL PROPERTIES

Color (APHA)	10
Condition	Clear
Sp. Gr. @ 25/15.5°C.	1.243
Total Acid Number, mg. KOH/g.	0.001
Inorganic Chlorides, ppm	0.03
Dielectric Constant @ 100°C., 60 Cycles	4.9
Resistivity @ 100°C., ohm/c/ @ 500 VDC 1 min. Electrification 0.1 inch gap	> 500
Refractive Index @ 25°C.	1.6151
Pour Point, °C.	-28
Water, ppm	25
Distillation, °C., Corrected:	
10% (by weight)	297°C
90% (by weight)	310°C
ASTM D1936	0.15
ASTM D1820	0.26
ASTM D2441	0.44
Thermal Chemical Chlorides	0.14
Viscosity @ 100°F (SUS)	44.2
Dielectric Strength @ 25°C	>50 KV

DSW 283451

STLCOPCB4064867