

MEMORANDUM

Reply to _____ Date 8/19/71 From P.C. Johnson To R.D. Adams - BBR
C.A. Homan - BBR
Subject SHREVEPORT ASBESTOS PERFORATED FELT

The record of 197.4 rolls an hour is quite an achievement. I would like to have consideration given to sending Perth Amboy personnel to Shreveport to get a little education of how to run asbestos felt. They could also have a few lessons on running organic felt.

I also would like to have Shreveport send a roll of samples of asbestos felt up to Carroll Homan. It would be comforting to know that we not only are breaking all kinds of production records but that we are also saturating the felt properly and have no obvious weaknesses such as wet edges, etc. I would like to have Carroll Homan find out just what the quality is on this product, particularly on this record run.

*Run Aug 13th
Nicolets Felt*

PCJ:F

*Wet edges from weaving, especially
at high speeds. Striker in within
24 hrs if not too wide - (max 3/8") no
wet edges are shipped.
PSL has checked rolls with wet edges
and found no tendency to tear or
unraveling -*

000476