

CG 01 CODE YE-698-D PKG

LOT MAY -0-81-E 1439

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
 YE-698-D (S) F. POST 4714/81
 ALTERNATE
 TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
242	5-20-81	1:40	JMH	2	92	93	54	54	54	1	1	1	1	1	1	1	1	1	1	1	1	1

SAMPLES
 DELIVER TO

SAMPLED BY
 RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
 (NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appears dry
 ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
 DELIVER TO COLOR TEST LAB

NO CARS PULLED
 SAMPLED BY
 RELEASED BY

NO DRUMS
 LUMP WGT 5716

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
 MAX. TEMP DEG F
 SET ROOF BLAST - GATE AT "9" FOR
 HIGH AIR FLOW

SCREEN RPM
 MAX. TEMP F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
 SAMPLES
 DELIVER TO CTL

DATE MIXED
 SAMPLED BY
 RELEASED BY

1439
41
231

0.00 *

3.45 +
0.12 -
3.41 +
0.12 -
3.47 +
0.12 -
3.33 +
0.12 -
3.38 +
0.12 -
3.29 +
0.12 -
3.25 +
0.12 -
3.27 +
0.12 -
3.44 +
0.12 -
2.99 +
0.12 -
3.30 +
0.12 -
3.37 +
0.12 -
3.02 +
0.12 -
3.76 +
0.12 -
45.05

14

45.05 +
3.26 +
0.14 -
3.31 +
0.14 -
3.24 +
0.14 -
2.86 +
0.14 -
57.16 *

4