

CUSTOMER # 2

* ORDERED
MORE OXY 200,
+ Calcium P-615
BOB
4-7-68

total	539	80
-------	-----	----

LAB TO WATCH WEIGHING & MIXING

SAMPLE TO LAB FOR CHECK

* COLOR + CHEMIGUM TO BE ADDED IN COOLING TUMBLER

HARDNESS 85+/-5

STOCK NO. 06011 -1

GOODYEAR BLK.#2

COMPOUNDED BY

01/22/88

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
105	VCP4797 90VCP 01 BLACK	2.00	1.54	1.48	4.00
165	VANSTAY 5515ND	1.00	.72	.74	2.00
166	FIRESHIELD H	3.00	.58	2.22	6.00
167	SANTOVAR A	.20	.19	.14	.40
168	ACRYLORD K120	5.00	5.15	3.70	10.00
169	KENAMIDE E	.50	.52	.37	1.00
90115	WINGSTAY 10029	.50	.38	.37	1.00
90122	FLECTOL H	.50	.47	.37	1.00
90447	DYPHOS XL	5.00	1.11	3.70	10.00
170	CHEMIGUM NBR P-615	27.25	27.53	20.19	54.50 A
159	OXY 200	47.75	34.35	35.38	95.50 A
156	CHEMIGUM NBR-P83	27.25	27.53	20.19	54.50 A
162	PLASTHALL P670	15.00	13.89	11.11	30.00 A

TOTAL	134.95	113.96	99.99	269.90
-------	--------	--------	-------	--------

1.23	-	PHYSICAL PROPERTIES
USE	-	SPEC. MIN. MAX.
REPLACES	-	SPECIFIC GR. 1.184
REASON	-	HARDNESS
COLOR	-	TENSILE
REQUIRMENTS TO MEET	-	ELONGATION
	-	MODULUS @
	-	MOONEY @
	-	SCORCH
	-	CURE
	-	STOCK CONTROL TEST
LAB	-	
COST	-	
MIXING	-	

CHARDO 01352

200 RESIN
P-615 Chemigum