

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko - AT Burl. Compound DATE August 19, 1969
 FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr
 SUBJECT Firestone 225 Resin H. H. Duhamel
 P. Gawason
 P. R. Scarito
 File

The results of Firestone 225 received on 8/18/69 and 8/19/69 are as follows:

<u>Properties</u>	<u>8/18/69</u>	<u>8/19/69</u>
Relative Viscosity	2.29	2.26
Gels	7	8
Dry Blend	6.8	6.0
Screen		
+40	2	Tr
+60	3	2
+80	31	37
+100	64	68
+140	88	92
+200	100	99
Thru	--	1

The particle size on 60 mesh screen is above our specification of 0-Tr, and should be monitored by the Compound plant for quality of the end product.

E. L. Kanyok
 E. L. Kanyok

ELK/rjl