

FRICTION PRODUCTS GROUP  
WINCHESTER, VIRGINIA  
APPENDIX #2

| <u>Sample No.</u> | <u>Field Lab.</u> | <u>Mix Used</u> | <u>% Long Fibers<br/>in Mix</u> | <u>% Short Fibers<br/>in Mix</u> | <u>Fiber Count<br/>&gt; 5μ/ml</u> |
|-------------------|-------------------|-----------------|---------------------------------|----------------------------------|-----------------------------------|
| 1                 | 1839              | #551D-333       | 55%                             | 45%                              | 1.46                              |
| 2                 | 1840              | #133-9          | 26%)                            | 74%)                             |                                   |
|                   |                   | #551D-333       | 55%)                            | 45%)                             | 1.75                              |
| 3                 | 1841              | #80 mix         | 100%                            | 0%                               | 4.10                              |
| 4                 | 1842              | #551C           | 56%                             | 44%                              | 1.73                              |
| 5                 | 1843              | #672-124        | -                               | -                                | 1.20                              |
| 6                 | 1844              | Blank           | -                               | -                                | 0.00                              |
| 7                 | 1845              | -               | -                               | -                                | 2.99                              |
| 8                 | 1846              | -               | -                               | -                                | 0.60                              |
| 9                 | 1847              | -               | -                               | -                                | 1.11                              |
| 10                | 1848              | #551D-333       | 55%                             | 45%                              | 1.68                              |
| 11                | 1849              | #80 mix         | 100%                            | 0%                               | 3.59                              |
| 12                | 1850              | #133-9          | 26%)                            | 74%)                             |                                   |
|                   |                   | #551D-333       | 55%)                            | 45%)                             | 1.46                              |
| 13                | 1851              | #551D-333       | 55%                             | 45%                              | 1.54                              |
| 14                | 1852              | #435-7          | Wet mix                         | Wet mix                          | 0.50                              |
| 15                | 1853              | #734-161        | Wet mix                         | Wet mix                          | 0.43                              |
| 16                | 1854              | #551CSC         | 56%                             | 44%                              | 1.24                              |
| 17                | 1855              | #693-555        | 57%                             | 43%                              | 0.97                              |
| 18                | 1856              | #693-555        | 57%                             | 43%                              | 0.74                              |
| 19                | 1857              | #551CSC         | 56%                             | 44%                              | 1.15                              |
| 20                | 1858              | #435-7          | Wet mix                         | Wet mix                          | 0.29                              |
| 21                | 1859              | #734-161        | Wet mix                         | Wet mix                          | 0.18                              |
| 22                | 1860              | Blank           | -                               | -                                | 0.00                              |
| 23                | 1861              | #238            | -                               | -                                | 2.02                              |
| 24                | 1862              | #551DSC         | 55%                             | 45%                              | 2.38                              |
| 25                | 1863              | #551D-333       | 55%                             | 45%                              | 1.75                              |
| 26                | 1864              | #47E            | -                               | -                                | 2.31                              |
| 27                | 1865              | #551D-333       | 55%                             | 45%                              | 0.84                              |
| 28                | 1866              | #551D-333       | 55%                             | 45%                              |                                   |
|                   |                   | #47E            | -                               | -                                | 1.31                              |
| 29                | 1867              | Blank           | -                               | -                                | 0.00                              |