

PACKAGE TICKET

CODE BP-565

LOT K2K-40

PQ	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		<u>8</u>	<u>1196</u>	<u>9</u>

STUMP

TOTAL NET WT. 1196

LUMP WT. 1215

PKG. N-CODE

PROD. SUPV.

DATE

OPERATOR

RP

11.1.81.22

23

0.0

1.49 +

1.50 +

1.49 +

1.56 +

1.52 +

1.47 +

1.44 +

1.49 +

008

11.96

		0.0
001		0.59 +
		0.59 ±

PRODUCT NAME = MONASTRAL BLUE B
(RESIN EXTENDED CPC FOR PLASTICS)
CG 20 CODE BP-565-D PKG

LOT K2K40

OCT 12 1982

EST. WT. 1248 LBS.

NON-BLEEDING

PROCESSES APPROVED BY
BP-565-D (A) BBK 11/20/81
XOC-23 TCP 07/02/82

MAKING NOTES

JOB NAME: 20BP565DPA

INSTRUCTIONS

= PRESSING =

RECORD

	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED					
CAKES USED					
WATER ON					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED					
EXPLAIN LOSSES					

#3 CLEAN PANS + CARS (IF USED FOR OTHER CAGES) R.D. TO INSIST.
HOSE OFF PANS BEFORE PANLOADING

SAMPLES JAR
DELIVER TO

SAMPLED BY
RELEASED BY

DRY 36 HOURS AT 170 DEG F.
DRY IN SECTIONS:

= DRYING =

LUMP: - OK - WET - SALTS - CONTAMINATED

TAKE COMPOSITE SAMPLES FROM EACH DRYER CAR, NOTE CODE, LOT, DRYER #, DATE, TIME
AND SUBMIT TO CTL FOR % MOISTURE

LEAVE IN DRYER WHILE MOISTURE RUN
IF 1% OR LESS MOISTURE OK TO PULL
DUMP IN NEW LIP'S WITH LINER (CAPER)

SAMPLES 1PT + 1ENV
DELIVER TO CTL

NOTE - FILL IN BELOW
ADDITIONAL DRYING HOURS REQUIRED

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 1215

MILL LSP 0.75" SCREEN 1700 RPM
MAX. TEMP 140 DEG F

SCREEN RPM
MAX. TEMP. F

GRIND WITH CO₂ AS PER DP#FA 0043

SAMPLE WITHOUT MIXING
SAMPLES 2 ENV & 2 PT CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

40
51
16

0.00 *
1.67 +
0.14 -/
1.72 +
0.14 -/
1.62 +
0.14 -/
1.57 +
0.14 -/
1.65 +
0.14 -/
1.67 +
0.14 -/
1.63 +
0.14 -/
1.74 +
0.14 -/
12.15 *