

EQUIPMENT USAGE

	<u>Total Usage</u> <u>1971-75 Av., %</u>	<u>Lost Time for Maintenance</u> <u>1971-75 Av., %</u>
<u>Dispersion</u>		
Process (117)	65.8	2.4
Swenson	76.7	6.9
Bowen 1	79.7	4.9
Bowen 2	78.8	4.9
<u>Suspension</u>		
Process	67.0	0.9
Finishing	78.8	2.8

URL 21076

Ref.: 4-11 (a)
4-11 (c)

DER:ddb
1/27/76

UNIROYAL CHEMICAL DIVISION

RESIDUAL VCM IN MARVINOL FINISHED GOODS

<u>Marvinol Type</u>	<u>PPM VCM, 1975 Av.</u>
15	899
19	1265
22	451
23	561
24	1352
5051	7.8
53	7.5
56	12.1
5008	5.1
5800	48.0

URL 21077

MARVINOL PRODUCT QUALITY

<u>Year</u>	<u>Off-Grade, %</u>	
	<u>Dispersion</u>	<u>Suspension</u>
1970	9.8	1.1
1971	8.3	2.1
1972	6.7	5.4
1973	5.6	14.0
1974	5.3	3.9
1975	7.3	1.4
Av.	7.2	4.7

URL 21078

Ref.: 4-11 (b)

DER:ddb
1/27/76