

**FINISHED PRODUCT
SPECIFICATION**

PRODUCT:

**MX-1915
SILICATED SUPEREX BLOCKS**

DIVISION **IND**

SPEC. NO.

PAGE NO.

3.

43✓

V. QUALITY REQUIREMENTS (Cont'd)

- D. Hardness (m. m. by Plastometer)** 0.4 max. (avg. 5 samples)
as received 0.5 max. (individual)
- E. Change after Soaking Heat**
1. Hardness (6 hrs. @ 1500°F) 0.9 m.m. maximum
2. Loss in weight (6 hrs. @ 1500°F) 10% maximum
- G. Linear Shrinkage (percent) (Tested on Unsilicated Block)**
1. After 24 hrs. @ 1900°F 3% max.

CANCELLED
2/13/53

VI. MARKING, PACKAGING AND LABELLING

- A. Marking** - Because of the small amount of taper on some blocks it is difficult to determine visually which is the wide face. To facilitate installation this face shall be marked by an "X".
- B. Packaging** - Cases or Cartons. Cases when sawdust is used.
- C. Labelling** - Stencil on Case or Carton
- Order No.
Number of pieces
Size or customer's item No.
Print or drawing No.
Customer's name and destination

RECEIVED
DEC 7 1952
E. R. WILLIAMS

**DEFENDANT'S
EXHIBIT**
OF-244

**PLAINTIFF'S
EXHIBIT**
K-1672

**X - INDICATES
CHANGE - REASON:**

New Specification

**AUTHORITY
FOR CHANGE**

Regular Approvals

FILE-HOLDERS	IND ENG.	PROD. SUPT.	PLANT FINANCE OFFICE	RESEARCH LAB.	DIR. QUAL. CONTROL	MR. QUAL. CONTROL	SUPR. QUAL. CONTROL
H. A. J. C.							

SUPERSEDES:

FORM 5013-7
PRINTED IN U.S.A.

Part of spec. 11-16-50.

DATE ISSUED

12-5-50