MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 22068 LOT 25-22-3

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	2	234	60	
	STUMP		2740	

TOTAL NET WT. 234 PKG. N–CODE

PROD. SPVR. DATE 1311 WHSE. OPER.

N 31790

0.T

89.+
101.+
111.+
85.+
96.+
88.+
87.+
98.+
102.+
120.+
110.+
96.+
90.+
89.+
76.+
98.+
70.+
124.+
87.+
87.+
36.+
135.+
94.+
108.+
106.+
82.+
135.+
74.+
2724.T

N 31790.01

DUP050292064

1 Car in dupe #93

N 31790.02

DUP050292065

32/105

CG 50 CODE YT-562-D PKG. ____

→ JAN 21 81 38723

EST. WGT. 2525 LBS.

2 2/2

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	YT-562-D (P)	BBK 01-16-78
		AMJ 12-14-78
	TYPED BY	
	emw121578	

MAKING NOTES

REMARKS

NAME: GREEN GOLD

NON-BLEEDING

INSTRUCTIONS — -PRESSING- — RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	105					STARTED	930 PM				
DATE	1-21					CAKES USED	60				
TIME	800A					WATER ON	3AM				
RELEASED BY	MDL					HRS. WASHED	10				
PRESS	32	33	35	36		OHMS	6500				
NO. OF CAKES	60	60	60	64		HRS. WASHED					
PRESS without AGITATION						OHMS					
WASH TO 4000 OHMS with 135-145°F water						HRS. WASHED					
TEST AFTER 9 HOURS						OHMS					
LOAD on 7 cars						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

OK

SAMPLES 8 oz
DELIVER TO Hold for P E

SAMPLED BY RELEASED BY

-DRYING-

Dry 20 Hrs at 200°F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appeared dry / Released 1/22/81

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 15

SAMPLES 8 oz
DELIVER TO Hold for P E

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 2740
RELEASED BY

-GRINDING-

MILL 8 HSP 1/8" RP SCREEN 3560 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F


EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can [redacted]

DATE MIXED 1-31-81
SAMPLED BY RELEASED BY

DUP050292066

N 31790.03



DUP050292067

N 31790.04

38723
51
197

0.00 *

2.13 +
0.14 ✓
2.29 +
0.14 ✓
2.19 +
0.14 ✓
2.26 +
0.14 ✓
2.16 +
0.14 ✓
2.19 +
0.14 ✓
2.01 +
0.14 ✓
2.09 +
0.14 ✓
2.10 +
0.14 ✓
2.09 +
0.14 ✓
2.10 +
0.14 ✓
1.42 +
0.14 ✓
23.35 *

12

N 31790.05

DUP050292068