

SWP GLOSS WHITE ANALYSIS (Rx 471)
Effective Sept. 12, 1939

Pigment by weight	65%
Vehicle by weight	<u>35%</u>
	100%
Composition of Pigment:	
*S-W Ozlo Lead-Zinc Pigment	45%
White Lead Carbonate	18%
Titanium-Magnesium Pigment	32%
Titanium Dioxide	<u>5%</u>
	100%
*Basic Sulphate White Lead	
Zinc Oxide	<u>16%</u>
	29%
	45%
Composition of Vehicle:	
Linseed Oil	89%
Japan Drier	<u>11%</u>
	100%