

- 54 -

PORTLAND OF SPECIALTY PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

ANTHRAZENE PAINT
Red Lead Paint (150%)
Percentage Formula : Working or Vat Formula
January 1941 to January 1942
January 1941 to January 1942

	<u>Percent</u>		<u>Gals.</u>	<u>Lbs.</u>
	69	95% Red Lead		903
		Raw Linseed Oil	40.2	
	70	Asbestine		300
	24	Aluminum Stearate		0.5
	<u>100</u>	500 Oil	10.8	
	31	Drier	5.4	
		Raw Linseed Oil	10.3	
Red Oil	79			
Red Lin.	15			
Drier	6			
	<u>100</u>			
	100			

White Shellac (1/2%)
Percentage Formula : Working or Vat Formula
January 1941 to January 1942
January 1941 to January 1942

	<u>Percent</u>		<u>Gals.</u>	<u>Lbs.</u>
	36	Alcohol	74	501.7
White Shellac	<u>100</u>	Leached Shellac		204
	100			
	64			
Alcohol	<u>100</u>			
	100			
	<u>100</u>			