

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky 787 LOT 34557

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>70</u>	<u>3500</u>		

STUMP

TOTAL NET WT. 3500 PKG. N-CODE ~~113~~ 01135

PROD. SPVR. WK DATE 3/4/40 WHSE. OPER. _____

22
240

CG 03 CODE KY-787-D PKG.

FEB 25 34557

EST. WGT. 1090 990 LBS.

OK
FP

[Handwritten signature]

Total Wgt. 3490# 3390

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSSES KY-787-D (B) Alternate	APPROVED BY FWK 9/22/76 DIG 9/27/76
	TYPED BY NF 2/12/77
MAKING NOTES	
REMARKS	

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	2-26-80				STARTED	1030PM				
TIME	10:20 PM				CAKES USED	116				
RELEASED BY	C. M.				WATER ON	1230PM				
PRESS	22	23	24	24	HRS. WASHED	18				
NO. OF CAKES	46	46	46	52	OHMS	2000				
PRESS with		AGITATION			HRS. WASHED					
WASH TO	2000	OHMS with	35-75°F	water	OHMS					
TEST AFTER	2	HOURS			HRS. WASHED					
LOAD	on 6 cars				OHMS					
					CAKE CONDITION	6				
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO cty for color

SAMPLED BY RELEASED BY *[Signature]*

-DRYING-

Dry 12 hrs at 220°F. Then Dry 8 hrs at 160°F.	LUMP: - OK - WET - SALTS - CONTAMIN. - E.
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	NO. CARS PULLED
DELIVER TO	SAMPLED BY
	LUMP WGT. 3493
	RELEASED BY <i>[Signature]</i>

-GRINDING-

MILL org HSP 3/32" RD	SCREEN 3500 RPM	SCREEN
MAX. TEMP. 150 °F		MAX. TEMP. °F
		EXPLAIN LOSSES
SAMPLE / WITHOUT MIXING	DATE MIXED	
SAMPLES 3 ENV & 3 P. can		
DELIVER TO C T L	SAMPLED BY	RELEASED BY

DUP050093836

N 26321.01

34557
41
324

0.00 *

2.70 +

0.14 -

2.62 +

0.14 -

2.71 +

0.14 -

2.55 +

0.14 -

2.75 +

0.14 -

2.69 +

0.14 -

2.65 +

0.14 -

2.48 +

0.14 -

2.62 +

0.14 -

2.66 +

0.14 -

2.62 +

0.14 -

2.64 +

0.14 -

2.60 +

0.14 -

2.60 +

0.14 -

34.93 *