

FORMULAE OF SPECIFIED PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER 'C'

Interior Gloss (Enamel)

Percentage Formula		Percentage Formula	
November 1940 to November 1941		December 1941 to June 1942	
	Percent		Percent
Pigment	50.5	Pigment	55.3
Lithopone	79.8	Titanium Dioxide	9.11
Titanium Dioxide	20.2	Lithopone	90.89
	100.0		100.00
Vehicle	49.5	Vehicle	44.7
Varnish and Oils	70.8	Varnish and Oils	71
Thinner and Drier	29.2	Thinner and Drier	29
	100.0		100
	100.0		100.0

Red Lead Paint

Percentage Formula

December 1940 to June 1942

	Percent
Pigment	69.1
Red Lead	38.4
Silica	30.8
Asbestine	30.8
	100.0
Vehicle	30.9
Boiled Oil	66.9
Raw Linseed Oil	26.7
Drier	6.4
	100.0
	100.0