

FORMULA RECORD			
Est. No.	Date	Rex. No.	Card No.
11-1-55	11-1-55	303	4
Name	Family	Trade Sales	See No.
600	4610 S. X	Customer	
150	20 L. Y. F.	To Match	Established Product
1	98	Made	Identical with Rex 832
		Weight Per Gal.	13.20
	1160 Base	Visc.	
		Barrel	Std. of Fineness
		35	2 F
		Gals. per hour	30"
		New Std. Sample Required	No
		Reason for Revision	To reduce grinding expense.
28	GALS. (1) (509)		
32	(45)		
5	(440)		
12	(148)		
8	(348)		
		Normal Output	100
		Est. Mfg. Loss	3%
		Approved	Formulator
		Supt.	H. B. Eimberken
		Label Analysis Checked - Date	

MANUFACTURING INSTRUCTIONS:				PRODUCTION			
Reduction: Amount		Reducer Used		Date	Slip No:	Amount	
Wood or Metal Int. or Ext.		Brush					
Application: Surface		Method: Spray					
No. Coats: Solid - 2		Undercoater Used:					
Drying Time: Touch 8-12 hrs.		Handle:		Recoat 18-24 hrs.			
Rab:		Sand:		Wrap:			
Baking Time and Temp:		Stencil:					
Gloss: Oil		Film:		Tough			
Special Tests							
FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND	11-6-35	608-6-37		ALLIED RESEARCH	11-6-35	608-6-37	
NEWARK				GIBBSBORO			
KENSINGTON				DAYTON	3-8-38		
OAKLAND				DETROIT			
DALLAS				LONDON			
LOS ANGELES				AUSTRALIA			
MONTREAL							
COSTA MESA							