VISCOSITY WORK SHEET

Item	P.T.No.	Date 4/13/54
Worker Jackie Harrison	Polymer Lucite	Solvent E.D.C
For Benjamins	Charge 1242	Temperature 25°
Viscometer No. 1	Efflux Time 236.6	Weight: Gross
Viscometer No. 2	Efflux Time 220.0	Tare
Viscometer No.	Efflux Time	Net 0.1250

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh.visc. or M.W.
4121-70-2	M31	1	289.8, 290.0, 289.6, 289.7	1.222	91,000
	VIII	2	269.1, 268.9, 268.9	1.222	91,000
	41	2	269.2, 269.2	1.222	91,000

PC-1

N38550