- CODE YE-698-D PKG

LOT MAY -0-81-E-1438

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

= PRESSING =

INSTRUCTIONS				RECORD					
VAT				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				STARTED					
TIME				CAKES USED					
RELEASED BY				WATER ON					
PRESS	2	92	93	HRS. WASHED					
NO.OF CAKES	54	54	54	OHMS					
PRESS WITH AGITATION				HRS. WASHED					
WASH TO 2000 OHMS WITH 35-75 F WATER				OHMS					
TEST AFTER 2 HOURS				HRS. WASHED					
LOAD ON 7 CARS				OHMS					
				CAKE CONDITION					
				NO CARS LOADED					
				EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

Color appears dry

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 18
LUMP WGT 5739

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1438

0.00 *

3.70 +
0.12 -
3.35 +
0.12 -
3.45 +
0.12 -
2.98 +
0.12 -
3.14 +
0.12 -
16.02 *

1438
41
85

3.25 +
0.14 -
3.28 +
0.14 -
3.49 +
0.14 -
16.02 +
25.62 *

25.62 +
3.32 +
0.14 -
3.33 +
0.14 -
3.23 +
0.14 -
3.24 +
0.14 -
3.65 +
0.14 -
3.48 +
0.14 -
3.49 +
0.14 -
3.70 +
0.14 -
3.19 +
0.14 -
2.54 +
0.14 -
57.39 *

DUP050095951