MONSANTO

FROM (LOCATION) St. Louis Research Dept.

DATE January 29, 1965

SUBJECT Ross and Roberts, Inc.

REFERENCE ECW/NWT, Ross & Roberts, Inc.
1/19/65 WR-65-15

TO E. C. Wilde - EWILD

cc: M. W. Farrar - Res 1
J. R. Darby - Res 3
A. W. M. Coaker - Res 3
N. W. Touchette - Res 3
W. F. Waychoff - WWAYC
W. B. Hicks - WHICK
H. R. Ford - HFORD

Adhesives - plastisol.

The following formulations were made up and tested for adhesion to spun glass fibers. A ten ml. wet film was applied to submitted samples, then fused at 175°C. for 5 minutes. No adhesion problem was encountered.

Opalon 410	100	100
Santicizer 679	70	56
Santoset I	-	14
Mark KCB	3	3
Paraplex G-62	3	3

The time required for this work was 3 hours.

Richard E. Schaefer

ds

DSW 586988

IN-10 REV. 8-64

STLCOPCB4092322