

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky-787 LOT 34597

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>70</u>	<u>3,500</u>		

STUMP

TOTAL NET WT. 3,500 PKG. N-CODE 1130

PROD. SVR. SWT DATE 3.13.80 WHSE. OPER.

23
243

CO 03 CODE KY-787-D PKG.

FEL 27 34597

EST. WGT. 1090 990 LBS.

OK

AP

[Handwritten signature]

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	
MAKING NOTES	

REMARKS

Total Wgt. 3490# 3390

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	243					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3-29-80					STARTED	1:30 PM				
TIME	9:50 PM					CAKES USED	46				
RELEASED BY	A.C.					WATER ON	9:50 PM				
PRESS	22	(23)	24	24		HRS. WASHED	9				
NO. OF CAKES	46	46	46	52		OHMS	2000				
PRESS with		AGITATION				HRS. WASHED					
WASH TO 2000		OHMS with 35-75°F water				OHMS					
TEST AFTER 2		HOURS				HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY RELEASED BY A.C.

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED 6
SAMPLED BY

LUMP WGT. 3408
RELEASED BY

-GRINDING-

MILL 039 HSD 3/32" RD SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES : CNV & 1 Pt. can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

DUP050093824

N 26317.01

34597

41

446

0.00 *
2.66 +
0.14 -
2.76 +
0.14 -
2.73 +
0.14 -
2.62 +
0.14 -
2.75 +
0.14 -
2.71 +
0.14 -
2.78 +
0.14 -
2.64 +
0.14 -
2.74 +
0.14 -
2.68 +
0.14 -
2.66 +
0.14 -
2.65 +
0.14 -
2.69 +
0.14 -
1.17 +
0.14 -
34.28 *