



JEANNETTE, PA.

MATERIAL SPECIFICATION No. 379

Date June 14, 1963

Sheet 1 No. SHEETS 2

Title: Asbestos Yarn - Waxed

- I. Scope: This specification covers a fire retardant product known as single asbestos yarn which is made from rubbed asbestos roving. The finished yarn shall have a waxed surface.
- II. Asbestos Content:
- Min. - 80%
- Max. - 84%
- III. Service Temperature: The material supplied to this specification shall be capable of withstanding a maximum temperature of 450°F.
- IV. Grade and Sizes: The material shall be ASTM D-299, underwriters grade.
- Sizes available shall be between 5 and 18 "cut" inclusive.
- V. Standard Specification: All provisions and requirements of ASTM D-299, latest revision, shall apply.

II. Asbestos Content:

Min. - 80%

Max. - - 84%

III. Service Temperature: The material supplied to this specification shall be capable of withstanding a maximum temperature of 450°F.

IV. Grade and Sizes: The material shall be ASTM-D-299, underwriters grade. Sizes available shall be between 5 and 18 "out" inclusive.

V. Standard Specification: All provisions and requirements of ASTM D-299, latest revision, shall apply.

Approved W. H. Hoffman

Approved XUCame

Approved _____

ET-00366

6D1

