RAW MATERIAL BULLETIN DRYWALL ACCESSORY PRODUCTS	ASBESTOS SG 210	BULLETIN NO: RMJ-047 DATE: 6/20/72 PAGE: 1 of 1
APPROVALS:		CANCELS: RM-J2D DATE: 9/15/69

APPROVED SOURCES: Union Carbide (SG-210)

PLAINTIFF'S EXHIBIT KG-21

SPECIFICATIONS:

1.	Magnetite (%)	2.5 maximum
2.	Reflectance, G. E. Photovolt (%)	68.0 minimum
3.	Dry Bulk Density, lbs/cu.ft.	5-6
4.	Wet Screen, Retain on	
	80 mesh (%)	0.8 maximum
	325 mesh	15.0 maximum

WARNING

Employees should wear respirators when handling, weighing and batching asbestos.

RAW MATERIAL BULLETIN DRYWALL ACCESSORY PRODUCTS	ASBESTOS 7RF10	BULLETIN NO: RM-J045 DATE: 6/20/72 PAGE: 1 of 1
APPROVALS:		CANCELS: RM-J045 DATE: 12/4/69

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

1.	Mixing Water Requirement	480 to 550
2.	Free moisture (200°F)	2.0%
3.	Color	Light Gray
4.	Grit	0.05% maximum. All passing 80 mesh screen
5.	Calcium carbonate (CO_2 method)	1.0% maximum
6.	Canadian screen	0.0-0.0-0.0-16.0
7.	pH (10% dispersion)	7-8
8.	Wet bulking	250-350

PLAINTIFF'S EXHIBIT HOBBY 11-4-98

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbest

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

PLTF 0216

RAW MATERIAL BUL'E.. DRYWALL ACCES. .RY PRODUCTS	ASBESTOS 7RF9	BULLETIN NO: RM-J046 DATE: 6/20/72 PAGE: 1 of 1
APPROVALS:		CANCELS: RM-J046 DATE: 12/9/69

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

1.	Mixing Water Requirement	450 to 550
2.	Free moisture (200°F)	2.0%
3.	Color	Light Gray
4.	Grit	0.05% maximum. All passing 80 mesh screen
5.	Calcium carbonate (CO_2 method)	1.0% maximum
6.	Canadian screen	0.0-0.0-0.0-16.0
7.	pH (10% dispersion)	7-8
8.	Wet bulking	200-300

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbestos.

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

PLTF 0217

RAW MATERIAL BULLETIN DRYWALL ACCESSORY PRODUCTS	ASBESTOS 7TF1	BULLETIN NO: RM-J050 DATE: 6/20/72 PAGE: 1 of 1
APPROVALS:		CANCELS: RM-J050 DATE: 1/26/71

USES: Joint and Finish Compounds, Texture Paints

APPROVED SOURCE: Philip Carey

ALTERNATE SOURCE *: Johns-Manville

SPECIFICATIONS:

1.	Mixing Water Requirement	330 to 370
2.	Free moisture (200°F)	2.0% maximum
3.	Color	Light Gray
4.	Grit	0.05% maximum. All passing 80 mesh screen
5.	Calcium carbonate (CO_2 method)	1.0% maximum
6.	Canadian screen	0.0-0.0-0.0-16.0
7.	pH (10% dispersion)	7.5-8.5
8.	Wet bulking	100-130

The following information is for Kaiser Gypsum Company personnel only:

Testing Schedule: Take a minimum of one 1/2 pound sample from each pallet in shipment, with a maximum of 20 samples. Test two random samples for grit and wet bulking. Test 10 samples for mixing water requirements. Retain a representative sample from each shipment for one year.

SAFETY: Employees should wear respirators when handling, weighing and batching asbestos

* Use Alternate Source in emergency only due to color. For regular use, Alternate Source must be rechecked by Research and "approved."

PLTF 0219

KAISER GYPSUM COMPANY, INC.

11525
DEFDOC
KAIS

INTER-OFFICE MEMORANDUM

TO	R.L. Allgood	W.L. Traub	DATE	March 1, 1965
	C.E. Caprye	J.H. Walton		
	J.D. Cassidy	R.J. Wiborn	FROM	L.R. Flicker
	J.D. Chambers	S.R. Witt	AT	KC 2482
	N.D. Dicks			
COPIES TO	D.H. Homan	cc: P.J. Franklin		
	J.F. Modaff	G.B. Kirk	SUBJECT	Health Hazards
	P.D. Orleman	J.C. Reilly		
		F.H. Schaper		

The attached material has been received from the Gypsum Association and is presented for your information.

In connection with protection against asbestos dust, it is advised to use a respirator with a filter especially designed for asbestos dust.

LRF:sb

PLAINTIFF'S EXHIBIT 7
40884
11-4-98