

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-907-D LOT 34159

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1740</u>	<u>1 -</u>	<u>T</u>	<u>- 299</u>	
<u>1720</u>	<u>1 -</u>	<u>T</u>	<u>- 109</u>	

STUMP

TOTAL NET WT. 3460 PKG. N-CODE _____

PROD. SPVR.

DATE

WHSE. OPER.

MP 217180 _____

22
244

CG 03 CODE KY-907-D PKG. _____

FEB-2 34159

EST. WGT. 1080 LBS.

OK
AP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-907-D (D) APPROVED BY
EWK 12/12/77
DCG 12/13/77

TYPED BY
rj 2/6/78

MAKING NOTES

REMARKS

TOTAL WGT. 3480#

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	244					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	2-4-80					STARTED	6:30 PM				
TIME	6:00 PM					CAKES USED	48				
RELEASED BY	JDC					WATER ON	10:00 PM				
PRESS	2	22	23	24		HRS. WASHED	3/8				
NO. OF CAKES	46	46	46	52		OHMS	2,500				
PRESS with						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					

SAMPLES 8oz Jar
DELIVER TO CIL for color

SAMPLED BY

RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 11
LUMP WGT. 3487
RELEASED BY BXX

-GRINDING-

MILL 939 HSR 178" RP SCREEN 3500 RPM
MAX. TEMP. 170 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PTCAN
DELIVER TO CIL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093999

N 26360.01

34159

41

252

0.00 *

3.48 +

0.14 -

3.40 +

0.14 -

3.53 +

0.14 -

3.53 +

0.14 -

3.36 +

0.14 -

3.42 +

0.14 -

3.51 +

0.14 -

3.57 +

0.14 -

26.68 *

26.68 +

3.39 +

0.14 -

3.32 +

0.14 -

1.90 +

0.14 -

34.87 *