

ONE

GALLON

O'BRIEN'S

Flexico

QUICK DRYING SUPER-ENAMEL

PRIMROSE

CONTAINS
O'BRIEN'S
EXCLUSIVE

Alki-therm

MADE IN U. S. A. • MANUFACTURED BY THE O'BRIEN CORPORATION • SOUTH BEND, INDIANA

Flexico is America's finest Enamel. Made with exclusive *Alki-Therm*, it may be used indoors or outdoors—on wood, plaster, metal, cement, hard wallboard, etc. Excellent for walls, woodwork, cabinets, furniture, boats, automobiles, etc. Use Brilliant White (non-yellowing) for touching up chipped stoves and refrigerators. Easy to apply. Dries quickly. Extremely durable and weather resistant. Apply with brush or spray.

NEW WOOD — apply one coat of O'Brien's White Surfacer or Double-Up Undercoat and finish with one or two coats of Flexico.

NEW PLASTER — apply one coat of O'Brien's Liquid Velvet Wall Primer and Sealer. Finish with one or two coats of Flexico.

NEW METAL — one coat of O'Brien's White Surfacer or Double-Up Undercoat followed with one or two coats of Flexico.

OLD PAINTED SURFACES IN GOOD CONDITION
— one or two coats of Flexico.

GENERAL DIRECTIONS — mix the enamel thoroughly before using and apply with a soft bristle brush. Sand and dust carefully between coats.

REGN. No. 7515

DATE _____

SURFACE PREPARATION — surfaces should be clean and dry, free of wax, oil, grease or soap compounds.

THINNING — Flexico is ready for use. If it appears too heavy and easier brushing is desired, thin accordingly with turpentine or O'Brien's Reducit.

DRYING — allow overnight drying between coats.

TINTING — Flexico Brilliant White may be tinted to light shades with O'Brien's Pure Liquid Oil colors.

CAUTION — don't intermix Flexico with conventional type enamels.

WARNING! FLAMMABLE
Keep Away from
Heat, Sparks, and Open Flame.
CONTAINS LEAD OR OTHER
COMPOUNDS HARMFUL IF EATEN.
Do not apply on toys, furniture,
interior surfaces which might
be swallowed by children. Use with adequate
ventilation. Avoid breathing
vapor or spray mist. Avoid
prolonged contact with skin. Wash
thoroughly after handling a
container. Do not use in
enclosed spaces. If container
closed when not in use.

FENICOL - PHENOLSE	
Phenol	98.26%
Phenol	79.73%
Phenol	20.23%
C. P. Chrome Yellow	100.00%
Vehicle	81.44%
*Alkyd Resin Solution	14.21%
*Alkyd Resin Solution	75.97%
Odorless Mineral Spirits	8.85%
& Driers	100.00%
***Varnish	
Non-Volatile, Modified	
Phenolic Resin	54.98%
China Wood Oil	43.02%
Volatile	100.00%
Odorless Mineral Spirits	
*Alkyd Resin Solution	
Non-Volatile; Seta Oil	60.00%
*Alkyd Resin Solution	40.00%
Volatile; Alkyd Resin	100.00%
Odorless Mineral Spirits	

THE O'BRIEN CORPORATION

SOUTH BEND, IND.
OKLA. CITY, OKLA.
BALTIMORE, MD.
SAN FRANCISCO, CAL.