#4

CHASE MACHINE

S.A.E. BRAKE LINING QUALITY CONTROL PROCEDURE

N-388F
H-350F



Test No. TR 16197

Prob. No Fm 1-5777

Date 8-30-79

Material 734-161

X473 J.M.

Sample No. New York State

Drum No. G.M.

	Wear Weight Grams	Data Thickness Inches
RANGE Stark	.26 - .33	.001 - .0095
Finish	6.76	.238
	6.45	226
Loss	.31	.010

Technical Notebook

Friction: Normal .401 - .455 Avg. 431 Hot 376 426 Avg. 408

SC1 02472