

6000 SUP

01519

Registered

Lowe Brothers
REG. U.S. PAT. OFF.
**HIGH
STANDARD
HOUSE PAINT**

WHITE 328

U.S. STANDARD GALLON

FOR EXTERIOR OR INTERIOR WORK

DIRECTIONS—The surface must be dry and clean. Remove loose paint. Putty nail holes after priming. Do not paint in damp, foggy or cold weather. Allow two days, and not more than ten days, between coats for drying.

MIXING—Pour off liquid into another vessel; stir remaining paste to uniform consistency; return liquid gradually, stirring well between additions.

IMPORTANT NOTES—This product to be used as a WHITE only—DO NOT TINT. For special colors, use High Standard House Paint Tinting White 348 shaded with Lowe Brothers Tinting Colors or Colors in Oil.

UNDERCOATS—For the priming coat on NEW WORK use High Standard Primer WITHOUT THINNING or High Standard House Paint thinned by the addition of one quart to one-half gallon of linseed oil to each gallon of High Standard House Paint, depending on the condition of the surface. For the first coat in REPAINTING use High Standard Primer WITHOUT THINNING, or High Standard House Paint which has been thinned by the addition of one or two pints of linseed oil to each gallon of paint; on porous surfaces a greater amount of linseed oil should be added.

FINISHING COAT—Use High Standard House Paint as it comes in the can.

THE LOWE BROTHERS COMPANY
DAYTON FACTORIES TORONTO

MADE IN U.S.A.

High Standard White 348 (By Weight)	63.0%
Pigment Vehicle	37.0%
Pigment (By Weight)	100.0%
Tinctorium Calcium	2.0%
Tinctorium Oxide	8.0%
Basic Sulfate	
White Lead	15.5%
Basic Silicate	
White Lead	2.5%
Zinc Oxide	19.0%
Magnesium Silicate	19.0%
Vehicle (By Weight)	100.0%
Raw Linseed Oil	2.0%
Heated Linseed Oil	2.0%
Mineral Spirits	2.0%
& Filler	2.0%