
CODE [illegible] LOT [illegible]

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	21	1438	11-46	
	STUMP		1503	

TOTAL NET WT. 1438 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	5/11/81	23


0.T
68.+
64.+
68.+
69.+
68.+
76.+
65.+
79.+
69.+
82.+
83.+
65.+
76.+
80.+
68.+
58.+
68.+
58.+
65.+
65.+
60.+
1448.T

38/967

CG 16 CODE RT-899-D PKG. ____

→MAY -0·81- Ξ1252

EST. WGT. 1491 ~~1500~~ LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	RT-899-D (C)	BBK 11-12-75
	(B) RC-13-A	DCG 11-12-75
TYPED BY	emw070279	

MAKING NOTES

REMARKS

NAME: MONASTRAL® VIOLET NON-BLEEDING

INSTRUCTIONS						-PRESSING- RECORD					
VAT	267					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-6-81					STARTED	9:15 PM				
TIME	5:30 PM					CAKES USED	60				
RELEASED BY						WATER ON	12:44				
PRESS	38	39				HRS. WASHED	5				
NO. OF CAKES	60	60				OHMS	5,000				
PRESS without AGITATION						HRS. WASHED					
WASH TO 5000 OHMS with 35-75°F water						OHMS					
TEST AFTER 4 HOURS						HRS. WASHED					
LOAD on 8 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	3 + 3				
						EXPLAIN LOSSES					
SAMPLES											
DELIVER TO						SAMPLED BY		RELEASED BY			

-DRYING-

Dry 18 hours at 220°F
Lock Lids

LUMP: - OK - WET - SALTS - CONTAMINATED

Dryer sections used:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 1428

SAMPLED BY RELEASED BY

-GRINDING-

MILL 1 HSP	0.066 RP SCREEN 3480 RPM	SCREEN	RPM
MAX. TEMP.	130°F	MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE	WITHOUT MIXING	DATE MIXED	
SAMPLES	2 Env & 1 Pt Can [redacted]		
DELIVER TO	CTL	SAMPLED BY	RELEASED 200 5-14-81

DUP050096882

899
1252
51
56

0.00 *

1.33 +
0.14 -
1.40 +
0.14 -
1.30 +
0.14 -
1.32 +
0.14 -
1.36 +
0.14 -
1.31 +
0.14 -
0.89 +
0.14 -
7.47 *

7.47 +
1.30 +
0.14 -
0.89 +
0.14 -
9.38 *

9.38 +
1.29 +
0.14 -
1.23 +
0.14 -
1.26 +
0.14 -
1.15 +
0.14 -
0.67 +
0.14 -
14.28 *

DUP050096883