MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky 787 LOT 38381

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2000	1	T—	273	
2010	1	T—	202	
1444	1	T—	158	
	STUMP	[illegible]	5811	

TOTAL NET WT. 5454 PKG. N—CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	/ /	

N34746

5/262 95-262

CG 03 CODE KY-787-D PKG. _____

→ DEC 23 80 38381

EST. WGT. ~~1921~~ _____ LBS.

AK
KB

5045

TOTAL WGT ~~6121#~~ (REQ _____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (S)	EWK 10-19-77
Alternate	DCG 10-25-77
TYPED BY	
JIC 11-4-77	

MAKING NOTES

REMARKS

NAME: KROLOR® YELLOW-MEDIUM **NON-BLEEDING**

INSTRUCTIONS

VAT	262
DATE	12-23-80
TIME	4 pm
RELEASED BY	
PRESS	96 95
NO. OF CAKES	70 72 72
PRESS WITH	AGITATION
WASH TO	2000 OHMS WITH 35-75°F WATER
TEST AFTER	4 HOURS
LOAD ON 10 CARS	

SAMPLES 1-8 oz. JAR
DELIVER TO CTL FOR COLOR

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8 AM				
CAKES USED	72				
WATER ON	3:30 PM				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7	6			

EXPLAIN LOSSES

SAMPLED BY 375 RELEASED BY A.K

-DRYING-

DRY 12 HRS AT 220°F.
THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No. Drums: 33

SAMPLES
DELIVER TO

NO. CARS PULLED 13 LUMP WGT. 5811

SAMPLED BY RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 env + 1 Pt Can
DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050105160



38.82 +
1.97 +
0.12 -
1.91 +
0.12 -
1.89 +
0.12 -
1.86 +
0.12 -
1.83 +
0.12 -
1.89 +
0.12 -
1.84 +
0.12 -
1.80 +
0.12 -
1.96 +
0.12 -
1.97 +
0.12 -
1.69 +
0.12 -
58.11 *



DUP050105162