

EDGE CODES

Friction Identification System for Brake Linings and Brake Blocks for Motor Vehicles – SAE J866a

SAE Recommended Practice

Report of Brake Committee approved March 1964 and last revised September 1966. Editorial change May 1967.

Scope – This SAE Recommended practice is intended to provide a uniform means of identification which may be used to describe the initial friction characteristics of brake linings and brake blocks for use on motor vehicles.

NOTE: It is emphasized that this recommended practice does not establish friction requirements for brake linings or brake blocks, nor does it designate other significant characteristics of brake linings or brake blocks which must also be considered in overall brake performance.

The basis for determining the friction coefficients for brake linings and brake blocks are tests in accordance with SAE J661.

Coding – The code will consist of two letters reflecting the friction coefficients as follows:

Code Letter	Coefficient of Friction
C	Not over 0.15
D	Over 0.15 but not over 0.25
E	Over 0.25 but not over 0.35
F	Over 0.35 but not over 0.45
G	Over 0.45 but not over 0.55
H	Over 0.55
Z	Underclassified

The first letter will represent normal friction coefficient and the second letter will represent hot friction coefficient.

Normal Friction Coefficient – Normal friction coefficient is defined as the average of 4 points on the second fade curve, located at 200, 250, 300, and 400 F.

Hot Friction Coefficient – Hot friction coefficient is defined as the average of 10 points located at 400 and 300 F on the first recovery; 450, 500, 550, 600, and 650 F on the second fade; and 500, 400 and 300 F on the second recovery.

NOTE: If any temperature point or points required to calculate friction coefficients are not reached in the prescribed time limit, the coefficient of friction value at 10 minutes shall be used to give the full number of points required.

EXAMPLE: A lining having a normal friction coefficient of 0.29 and a hot friction coefficient of 0.40 would be coded "EF".

Location of Code – The appropriate code designation will be marked on an external contacting surface in letters not less than 0.125 in. in height.

RECEIVED

MAR 22 1967

SALES DEPT.

Abex FRICTION PRODUCTS

P. O. Box 3250, Winchester, Virginia 22604

NOVO16415