Organic Research Department

August 22, 1960

R.E. Hatton - Res. 1
E.M. Emery - Res. 2
C.M. Edelblut - Anniston

Santowax M, Lot C-1

Mr. Malcolm McEwen - B-2-N

The gas chromotographic analysis of the Santowax M sample from Anniston is as follows:

ortho terphenyl	0.3% by weight
meta terphenyl	93.1%
para terphenyl	6.6%

No low boilers or high boilers were found. This assay is very similar to the lot which was analyzed for Canadian General Electric last February.

A. M. Ellenburg
Research Department

bl
8/23/60

0067896

TOWOLDMON0056720