PLAINTIFF'S EXHIBIT

USG-1827

DURABOND JOINT COMPOUND

(OLD DESIGNATION—DURABOND JOINT COMPOUND)

A polyindurate type formulation for embedding and filling PERF-A-TAPE reinforcement, fasteners, metal cornerbeads and drywall trims over gypsum wallboard.

FREIGHT SHIPPING BAG
Meeting requirements of
APPLICABLE FREIGHT CLASSIFICATION
Guaranteed by No. 1622137

73 84

DIRECTIONS FOR USE

Use drinkable water and clean mixing equipment. Mix powder thoroughly into water until powder is completely wet. After soaking for a few minutes, re-mix until smooth. First coat over tape of DURABOND Joint Compound — Taping may follow embedding coat immediately.

WATER PROPORTIONS PER 25# BAG

Hand Tool Application	Approx. 13½ pts.
Mechanical Taping	Approx. 17½ pts.
Mechanical Fill Coat	Approx. 15½ pts.

BASIC CAUTIONS

- MIX ONLY SUFFICIENT COMPOUND TO BE APPLIED IN APPROXIMATELY 2½ HOURS.
- DO NOT RE-TEMPER MIX.
- DO NOT INTERMIX WITH OTHER JOINT COMPOUNDS — IN WET OR DRY FORM.
- USE ONLY CLEAN WATER, MIXING EQUIPMENT AND TOOLS TO AVOID CONTAMINATION.
- HARDENING ACTION CANNOT BE PREVENTED OR DELAYED BY DILUTION WITH WATER.
- CLEAN TOOLS AND CONTAINERS IMMEDIATELY AFTER USE AND PRIOR TO HARDENING.
- USE ONLY DURABOND JOINT COMPOUND - TOPPING, USG READY MIXED JOINT COMPOUND - ALL PURPOSE, USG JOINT COMPOUND - TOPPING OR USG JOINT COMPOUND - ALL PURPOSE FOR FINISHING COAT.
- MINIMUM AIR, WATER, MIX AND SURFACE TEMPERATURES OF 45° F. MUST BE MAINTAINED WITHIN WORKING AREAS UNTIL JOINTS ARE COMPLETELY DRY.

For extra information, consult U.S.G. literature or your local U.S.G. representative.

For warranty, disclaimer and notice requirements, read current USG instructions and specifications, copies of which are available free upon request.

CAUTION

CONTAINS ASBESTOS FIBERS.
AVOID CREATING DUST.
BREATHING ASBESTOS DUST MAY CAUSE SERIOUS BODILY HARM.

UNITED STATES GYPSUM
CHICAGO, ILLINOIS 60606 PRODUCED IN U.S.A.

GP040 14

25
LBS. NET WT.

JOINT COMPOUND

TAPING

UNITED STATES GYPSUM

CP040 1924

*Reg.