cc: C. I. Hayden
S. M. Lillis
H. E. Dehr
L. S. Dymitro

March 11, 1970

To: S. G. Cerve

From: J. C. Toman

SUBJECT: ASBESTOS - Fiber
VICTOPAC - Materials

re: Lake Asbestos #5K5 Fiber
(Project 844986)
Blanking Characteristics

This is a follow-up to our note of February 24, 1970, on this subject.

Enclossd you will find an assortment of gasket blanks from VICTOPAC made with Lake Asbestos #5K5 vs. J-M #5K-02. Also enclosed are samples discs of these materials which were delaminated in order to permit examination of the sheet formation; note the better fiber coverage with J-M #5K-02 which results in better blanking characteristics.

We suggest you make your own extended evaluation of this particular phase of the Lake Asbestos on the next trial car which you will be receiving.

Materials Engineering

J. C. Toman

pt