

ASBESTOS
Product Brochures
1970

PLAINTIFF'S EXHIBIT

GP-1512

SGP 0022889

**GP GEORGIA-PACIFIC
BESTWALL**




GYPSUM WALLBOARD

FOR WALL AND CEILING SYSTEMS



GYPSUM QUARRY FT. DODGE, IOWA

- ▲ **Wallboard Products**
- ▲ **Joint System and
Accessory Products**
- ▲ **1/4" Incombustible
Gypsum Sound
Deadening Board**
- ▲ **G-P/Eternawall™**
- ▲ **Tile Backer Board**
- ▲ **G-P Bestwall
Steel Stud Details**
- ▲ **Technical Data**
- ▲ **Construction Systems**
- ▲ **Ceiling and Floor
Assemblies**



SGP 0022890



WALLBOARD PRODUCTS

Products	Thickness	Widths	Lengths	Edge	Description
G-P/Bestwall Regular Wallboard	1/4" 3/8" 1/2" 5/8"	4'	6' to 16' in even feet	T, S, B	G-P/Bestwall Regular Gypsum Wallboard is manufactured with Tapered or Square Edges and faced with a strong, cream-colored paper which will accommodate any type of decorative treatment. The back paper, which is gray, is as strong as the face paper. The 1/2" and 3/4" wallboard with Tapered edges is recommended for single layer application in new construction. Tapered edges are designed to be reinforced with G-P/Bestwall Joint System products which lend itself to a smooth, seamless surface. Square edges are recommended for use where exposed joints are acceptable. The resistance to fire exposure and sound transmission increase with the use of greater board thickness and the number of layers of board used. (See the Technical Data Charts on pp. F/10 thru F/13.)
G-P/Bestwall Firestop®	1/4" 3/8"	4' (2' on order)	6' to 16' in even feet	T, S, B	G-P/Bestwall Firestop carries a 45 minute to 3 hour fire resistant rating in various wood and steel wall and floor/ceiling assemblies. Unexpanded vermiculite in the core, balances gypsum shrinkage by expanding when exposed to heat, while the textile glass filaments keep the core intact even after its chemically combined water has been released, giving a thermal stabilized core. See pages F/10 thru F/13 for fire resistive ratings obtained by various Firestop assemblies.
G-P/Bestwall 1/4" Gypsum Sound Deadening Board	1/4"	4'	8'	S	G-P/Bestwall 1/4" Incombustible Gypsum Sound Deadening Board meets the requirements of the most sophisticated sound control systems available with the added convenience of being one of the easiest sound control materials to install. It is designed and formulated for high sound transmission loss, structural strength and incombustibility. It has a distinctive green face paper. When applied over 2 1/2" steel studs or 2 x 4 wood studs, one layer of 1/2" G-P/Bestwall Firestop Type XXX over one layer of 1/4" Gypsum Sound Deadening Board gives a 1-hour fire resistive wall and a 45 S.T.C. Refer to the brochure "Sounds Great" for other assemblies with S.T.C. ratings up to 55.
G-P/Bestwall Regular Tile Backer Board	1/2"	4'	8', 11' 12'	T	This is a water-resistant gypsum product with a light blue face paper, designed for use as a base for the adhesive application of ceramic, metal or plastic tile. The gypsum core consists of incombustible gypsum rock, combined with an emulsion giving high water resistance. This new G-P/Bestwall product is ideal for bathrooms, kitchens, powder rooms and other moisture areas. G-P/Bestwall Tile Backer Board can be erected as easily as wallboard and requires no finishing of joints or nail heads with joint treatment nor further waterproofing under tile applied adhesively unless required by local code.
G-P/Bestwall Firestop Tile Backer Board	3/8"	4'	8', 11' 12'	T	This contains the factory treated water-resistant core and treated face and back paper plus the addition of unexpanded vermiculite and glass fiber reinforcement which gives increased fire protection and strength. Where fire rated assemblies are required in areas subject to moisture, such as partitions between bathrooms and other interior areas, most building codes allow the use of G-P/Bestwall Firestop Tile Backer Board. The use of 3/8" Firestop Tile Backer will give a 1 hour fire rating.
G-P/Bestwall Regular Insulating Wallboard	3/4" 1 1/2" 1 3/4"	4'	6' to 16'	T, S	Regular Insulating Gypsum Wallboard is regular gypsum wallboard, with bright aluminum foil laminated to the back surface. In a single layer application it provides the advantages of regular gypsum wallboard plus having effective insulation and vapor barrier qualities. A separate and continuous vapor barrier automatically ascends on the warm side of the wall when G-P/Bestwall Insulating Gypsum Wallboard is applied. The aluminum foil, facing a 3/4" minimum space, reflects 90% of radiant heat, providing insulation qualities equal to 1/2" of fiberboard insulation (tested by U.S. Bureau of Standards). Panels must be installed with foil side against the studs. To have reflective insulation value, FHA requires the foil to face a minimum air space of 3/4".
G-P/Bestwall Firestop Insulating Wallboard	3/8"	4'	6' to 16'	T, S	This is the regular insulating gypsum wallboard with the addition to the core of unexpanded vermiculite and glass fiber content for increased fire protection. Through the proper use of this product desired fire-rated assemblies can be achieved.
G-P/Bestwall Regular Eternawall™—Vinyl Surfaced Wallboard: Standard Line	1/2" (Special order 3/4" & 5/8")	4'	8' (Other lengths available on special order.)	V, S	Colors—Avocado, Gold, Flax, White, Beige, Stucco, Buff, Willow Green, Fawn, Snowdrift White, Alabaster, Tangerine, Cherry, Pecan and American Walnut. This panel has the vinyl surface factory laminated to Regular Gypsum Wallboard. Available in a variety of colors and textures, it provides beauty and utility to commercial, institutional and home interiors. Eternawall is strong and resilient. The solid gypsum core is incombustible. It has a standard flame spread of 30, with a rating of 25 available on special order. Eternawall colors won't fade. The deep linen-textured vinyl surface can be scrubbed without damage to color, texture or design. Because of its ability to take hard wear and to resist stains, Eternawall is ideal for restaurants, hotels, clubs, and hospitals as well as home use. It is also ideally suited for movable partitions.
Decorator Line	1/2" (Special order 3/4" & 5/8")	4'	8' (Other lengths available on special order.)	V, S	Colors—Available in 15 patterns and over 200 decorator colors. Samples available upon request. The lowest cost for Decorator Line panels is based on a minimum order of 12,000 sq. ft. in one color and pattern. Allow eight weeks lead time. Note: "Monolithic" type Eternawall is available in both the standard and decorator colors on special order of 12,000 sq.ft. or more, in one color or pattern. Allow 12 weeks lead time.

SGP 0022891


Products	Thickness	Widths	Lengths	Edge	Description
G-P/Bestwall Firestop Eternawall—Vinyl Surfaced Wallboard	1/2" 5/8"	4'	8' (other lengths available on special order.)	V, S	This panel has the vinyl surface factory laminated to a Firestop panel which has unexpanded vermiculite and glass fibers added to the core to give it additional fire resistance. With this technically designed gypsum core, a 1 hour or greater fire rating may be obtained on wall assemblies. Same colors available as with regular Eternawall. Flame spread of 25 available on special order.
G-P/Bestwall Firestop Gypsum Sheathing	1/2"	2' and 4'	8' and 9'	S, T & G	Treated —G-P/Bestwall Firestop Gypsum Sheathing consists of incombustible gypsum rock combined with an asphalt emulsion to provide high resistance to water. All G-P/Bestwall Firestop Gypsum Sheathing meets ASTM C79-67, including requirement for water resistance. This eliminates the need for building paper (except where required by local building code). An untreated gypsum sheathing is available. The 2' wide sheathing is made with precision-cut tongue and groove edges to provide a structurally strong and stable wall. "V" tongue and groove edges fit snugly, minimizing wind infiltration. The 4' wide square edge sheathing, applied vertically, completely eliminates the need for corner bracing. It is designed to meet requirements of FHA Technical Circular 12.
G-P/Bestwall Gypsum Firestop Backer Board	1/2" 5/8"	2' and 4'	8' to 16'	S, T & G	G-P/Bestwall 1/2" Firestop Gypsum Backer is used as a backing for decorative surface treatments of acoustical plasters, tile, plywood and various veneers. A single layer application of 5/8" G-P/Bestwall Firestop Gypsum Backer on both sides of wood or steel framing, enables loadbearing or non-loadbearing wall assemblies to resist temperatures rising to 1700° F. in the ASTM standard time temperature curve for one hour. Firestop Gypsum Backer consists of a gypsum core with unexpanded vermiculite, reinforced with literally miles of high tensile strength glass fibres, firmly bonded to a fibrous gray paper on both sides.
G-P/Bestwall Regular Backer Board	3/8" 1/2" 5/8"	2' and 4'	8'	S	G-P/Bestwall Gypsum Backer, designed for first or base layers in field lamination of gypsum wallboards, acoustical tile and other compatible materials with adhesives, provides low cost, level surfaces for further decorative treatments. It may be applied over loadbearing or non-loadbearing wood or metal framing with nails, screws or staples.
G-P/Bestwall 1" Coreboard	1"	2'	Custom cut up to 14'	S, T & G	1" Gypsum Coreboard is available in two styles. a. A homogenous core with a tongue and grooved joint. b. Two layers of 1/2" backer board, laminated. 1" Gypsum Coreboard is used for the core material in various, all-gypsum partition assemblies.
G-P/Bestwall Grid Board	3/8"	23 3/4"	23 3/4"	S	Regular G-P/Bestwall Wallboard is fabricated as an economical, lay-in panel, for suspended ceiling systems. Vinyl covered available on special order.
G-P Wallboard Edges		T—Tapered S—Square B—Beveled (Special Order) V—Modified Beveled Edge			

SGP 0022892

GEORGIA-PACIFIC GYPSUM RESEARCH LABORATORY, Portland, Oregon



THIS IS WHERE NEW PRODUCTS DEVELOP! No matter how great a product is, it still must change to meet the needs of tomorrow. In gypsum, this means better fire con-



trol, better sound control and better products that will conform to the higher standards of tomorrow's construction.



G-P/Bestwall — Triple Duty Joint Compound

G-P/Bestwall Triple Duty Wallboard Joint Compound is a vinyl multi-purpose joint system product. A single bag offers taping, topping and texturing. It can be used for all coats in the reinforcing and concealing of joints in gypsum wallboard construction. The binder in Triple Duty, being a vinyl, gives this product a wet life of 30 to 60 days duration. This allows pre-mixing in large quantities prior to application. Triple Duty can be applied using standard hand or mechanical tools. There is low shrinkage and it is easily sanded. When the application is completed, the surface is ready for priming and decoration as desired with no further preparation necessary. **Coverage:** 60 lbs. per 1,000 sq. ft. (12-50 lbs. per 1,000 sq. ft. when used as a texturing material.)

Lb. Package—25 and 50



G-P/Bestwall — Bedding, Topping Compound

G-P/Bestwall Joint System products are designed to conceal joints and nail heads and "surface-weld" wallboard panels together. Properly used, these products assure smooth, seamless appearance of walls and ceilings, with joints as strong as the wallboard itself.

Bedding Compound — Designed to provide maximum adhesion of tape to the joints. It spreads smoothly and may be hand or machine applied. **Coverage:** 15 lbs. per 1,000 sq. ft. (Used in conjunction with 45 lbs. of Bestwall Topping Compound.)

Topping Compound — Used for finishing taped joints and spotting nail heads. Sanding is unnecessary if carefully applied. It is long working with low shrinkage. **Coverage:** 45 lbs. per 1,000 sq. ft. (Over 15 lbs. of Bestwall Bedding Compound.)


Lb. Package—25



G-P/Bestwall — Ready Mix Joint Compound

Ready Mix Joint Compound is an easy-working material for the filling of joints, and embedding the joint reinforcing tape in gypsum wallboard construction. Furnished in cans and cartons ready to use, this stable, all-purpose compound is also excellent for use in covering nail heads and forming interior and exterior angles. Ready Mix Joint Compound assures a standard mixture for uniform workability throughout the job. It has a long wet life and will not spoil even when the container is left opened. Ready Mix Joint Compound is completely compatible with the G-P/Bestwall 1-Day Wallboard Joint Compound and may be used for the topping coat over G-P/Bestwall 1-Day Wallboard Joint Compound. Ready Mix Joint Compound produces an excellent surface for any type of decoration. For best results, the surface should be primed before being decorated.

Package—1 and 5 gal. cans, 4 gal. cartons



G-P/Bestwall — All Purpose Joint Compound

G-P/Bestwall All Purpose Joint Compound is used for bedding tape, topping, corner bead, nail spotting and texturing. When taping be sure the compound under the tape, and the first coat over the tape is thoroughly dry before applying the next coat over the joints. When used for texturing, for best results, apply a vinyl primer to the entire area before texturing. The texture may be applied with a roller, sponge, brush or other suitable implement depending on the type of configuration desired. **Coverage:** 60 lbs. per 1,000 sq. ft.

Lb. Package—25; 18 lbs. with 250' tape



G-P/Bestwall — One Day

G-P/Bestwall 1-Day Wallboard Joint Compound makes possible the taping and finishing of all wallboard joints within a single day. It is used for all coats preceding the final coat. The compound, a "setting" material, rather than the conventional drying type material, is formulated to set and harden in 2½ to 3 hours. When hardened, G-P/Bestwall 1-Day Wallboard Joint Compound **will not shrink**. This solves a major problem of wallboard installation, by eliminating days of heating unfinished homes and buildings, time lost traveling to and from jobs, and long delays while waiting for conventional materials to dry and harden. And because there is no shrinkage, quantity of compound and number of coats applied, may be reduced. For best results, use a primer sealer over surface before painting or texturing.


Lb. Package—25

G-P/Bestwall — Laminating Compound

G-P/Bestwall Laminating Compound is an exclusive product formulated to assure adhesion between sheets of wallboard. It is a casein base dry powder product, requiring addition of water only. Easy to mix and easy to apply, it forms a permanent, positive bond. G-P/Bestwall Laminating Compound has been proven effective through many years of actual field use. **Coverage:** Approx. 35 lbs. per 1,000 sq. ft.

Lb. Package—25

SGP 0022893



G-P/Bestwall — Grabit

G-P/Bestwall Grabit is an adhesive which permits direct attachment of gypsum wallboard to masonry walls. It may be used on poured concrete, cinder block or concrete block walls which are reasonably straight and true and are free from surface treatment, decorations, or protrusions. Grabit may be used on exterior walls which are above grade level without waterproofing. Grabit can be used to adhere gypsum wallboard to polystyrene insulation material. Adhesion is secure and permanent, with no need for furring strips or fasteners. After being mixed with water as directed, Grabit can be applied with blade or caulking gun. Only four 1" ribbons are needed for each 4' wide wallboard panel. The adhesive fills in all normal irregularities in the masonry. In 3 to 4 hours, Grabit sets hard, and joint taping and finishing operations may then be started. This adhesive may be used wherever there is need to attach gypsum wallboard to masonry walls: in homes, apartments, hotels, offices, and plants. **Coverage:** Up to 1/4 lb. per sq. ft. depending on roughness of base surface.

Lb. Package — 50

G-P/Bestwall — Texturing Materials

G-P/Bestwall Bestex A, B, C and D are texture materials designed to produce various texture finishes over drywall construction.

Bestex A—contains no aggregate and can be used for both hand and spray application to produce textures such as stipple, swirl, spatter and orange peel finishes.

Bestex B—contains a small amount of aggregate and produces medium coarse textures such as sand finishes.

Bestex C—contains a large amount of aggregate and is used for coarse textures such as simulated acoustic finishes.

Bestex D—a texture with coarse aggregate for simulated acoustic ceilings.

B, C and D textures are for spray application only. All three textures produce hard surfaced, white, decorative finishes that have excellent light reflective qualities and hiding power. If desired, Bestex textures can be painted with latex or vinyl paint. **Coverage:** Bestex A-12-50 lbs. per 1,000 sq. ft. depending upon texture. Bestex B, C and D Finishes approx. 300 to 500 sq. ft.

Lb. Package — Bestex A 25 lb., Bestex B, C, D, 40 lb.

G-P/Bestwall — Drywall Screws

G-P/Bestwall Drywall screws are now available in a variety of sizes for every type of wallboard application. These screws are designed especially for drywall construction whether it be gypsum to gypsum, gypsum wallboard to metal or gypsum wallboard to wood framing. The special patented bugle head screws used when attaching wallboard, reduces the possibility of damaging the paper and produces a uniform depression for proper and easier spotting. The self-tapping quality of the screws effect rapid application when attaching wallboard to metal studs.

SPECIFICATIONS FOR WALLBOARD JOINT TREATMENT

Scope

All walls and ceiling surfaces are included. Furnish all labor and material necessary to reinforce and conceal joints between gypsum wallboards and cover nailheads in a first-class workmanship manner.

Materials

1. One-Material Treatment—G-P/Bestwall Joint System Compound Triple Duty Joint Compound, or G-P/Bestwall Ready Mix Joint Compound. Used for bedding and for spotting nailheads.

2. Two-Material Treatment—Apply G-P/Bestwall Wallboard Joint Compound, Triple Duty Joint Compound, Ready Mix Joint Compound, One Day Wallboard Joint Compound or Bedding Compound, and embed tape leaving uniform thickness of material under tape. Cover nail or screw heads in field of board at each application of material in joints.

(If joints are irregular or have wide cracks in some places and boards are not in same plane apply G-P/Bestwall Wallboard Joint Compound, Triple Duty Joint Compound, G-P/Bestwall Bedding Compound to taper edge joints, end joints and nail heads. Shear off surplus leaving no

material on high edges. Allow 12 hours drying before taping, leaving uniform depth of taper for uniform shrinkage of joint finishes over and under tapes.)

SGP 0022894

Jointwork

When compound has dried completely, cover taped joints with Wallboard Joint Compound, Triple Duty Joint Compound, Ready Mix or Topping Compound. (When 1-Day Wallboard Joint Compound is used, the taped joint can be covered as soon as initial coat is set and before it is dry.) Shear off surplus leaving uniform coverage over tape with edges well feathered.

When preceding coats are completely dry (where 1-Day is used it is only necessary for it to be hardened, not completely dry) cover joints second time with Wallboard Joint Compound, Triple Duty Joint Compound, Ready Mix Joint Compound, or Topping Compound. Shear off surplus leaving smooth, well feathered joint.

For best results and more uniform suction for decoration apply skim coat of wallboard Joint Compound, Triple Duty Joint Compound, Ready Mix Joint Compound or Topping Compound over entire surface shearing off excess material tightly.

1/4" INCOMBUSTIBLE GYPSUM SOUND DEADENING BOARD

Bestwall Gypsum Sound Deadening Board meets the requirements of the most sophisticated sound control systems available with the added convenience of being one of the easiest sound control materials to install.

Only 1/4" in thickness, Bestwall Gypsum Sound Deadening Board is specially designed and formulated for high sound transmission loss, not to mention its contribution towards

the structural strength and fire resistance of a construction.

1/4" Gypsum Sound Deadening Board has been tested in several assemblies with excellent results. Below are examples of the significant results. Others are listed under Technical Data, pages 10 through 13.


For test data on other wall assemblies, write for the brochure "Sounds Great"

WOOD STUD PARTITION

STC 45

FIRE RATING

1 Hr. Combustible
Test UL No. 30



SOUND TEST DATA

Test No.: BW-27FT
Date: July 6, 1967
Conducted By: Geiger & Hamme, Inc.
Test Partition: Height: 9'
Width: 14' 1/2"
Thickness: 5 3/4"
Weight: 7.60 lbs./sq. ft.
Sound Transmission Class 45
9 Frequency Average 43.1
11 Frequency Average 45.6


1. Nail 2" x 4" wood studs 16" o.c. to 2" x 4" wood plates at the floor and ceiling.
2. Apply a single layer of 1/4" Bestwall Gypsum Sound Deadening Board vertically to both sides and secure with 5d-c.c. nails spaced 12" at studs and plates. Joints should be staggered.
3. Apply a single layer of 1/2" Bestwall Firestop Type XXX wallboard or Firestop Eternawall vertically to both sides, over the 1/4" Gypsum Sound Deadening Board, by strip laminating with G-P Bestwall Laminating Compound. Vertical joints of the 1/2" Firestop should fall between the wood studs and should be nailed at top and bottom plates using 4d coated nails spaced 6" o.c.
4. Tape and finish in the approved manner.

STAGGERED WOOD STUD PARTITION

STC 52 (with insulation)
STC 47 (no insulation)

FIRE RATING

1 Hr. Combustible (Est)



SOUND TEST DATA

Test No.: BW-29ST (no insulation)
Test No.: BW-30ST (with insulation)
Dates: March 29, 1968-April 5, 1968
Conducted By: Geiger & Hamme, Inc.
Test Partition: Height: 9' 0" Weight: 8.79 lbs./sq. ft.—
Width: 14' 1/2" (no insulation)
Thickness: 7 1/4" 8.92 lbs./sq. ft.—
(with insulation)
Sound Transmission Class 47 (no insul.)
Sound Transmission Class 52 (with insul.)
9 Frequency Average 43.6 (no insul.)
9 Frequency Average 47.7 (with insul.)
11 Frequency Average 45.2 (no insul.)
11 Frequency Average 48.9 (with insul.)


1. Nail 2" x 4" wood studs staggered 8" o.c. on opposite sides of 2" x 6" wood plates.
2. Apply single layer of 1/4" Bestwall Gypsum Sound Deadening Board vertically to both sides, joints offset 8" on opposite sides, by nailing with 4d nails 12" o.c. at studs and plates.
3. Apply a single layer of 1/2" Bestwall Firestop Type XXX wallboard vertically to both sides over the 1/4" Bestwall Gypsum Sound Deadening Board by strip laminating 16" o.c. with Laminating Compound. Vertical joints of 1/2" Bestwall Firestop Type XXX should fall between the wood studs on each side and should be nailed at top and bottom plates with 5d nails 6" o.c.
4. Tape and finish in the approved manner.
5. On Test BW-30ST with STC 52, 1 1/2" insulation is applied in stud cavity with vapor barrier stapled to stud face.

METAL STUD PARTITION

STC 45

1 Hr. Incombustible
#T3854

1 Hr. Incombustible
UL No. 32



SOUND TEST DATA

Test No.: BW-16FT
Dated: July 21-28, 1966
Conducted By: Geiger & Hamme, Inc.
Test Partition: Height: 9'
Width: 14' 1/2"
Thickness: 4"
Weight: 7 lbs./sq. ft.
Sound Transmission Class 45
9 Frequency Average 44.3
11 Frequency Average 46.9


1. Set Bestwall 2 1/2" steel studs 24" o.c. into Bestwall 2 1/2" floor and ceiling track.
2. Apply 1/4" Bestwall Gypsum Sound Deadening Board vertically to both sides of partition and secure with Bestwall 1" Type "S" drywall screws spaced 12" o.c. Stagger joints.
3. Apply 1/2" Bestwall Firestop Type XXX or Firestop Eternawall vertically both sides, joints staggered, to the 1/4" board using 1 1/4" Type S drywall screws 12" o.c. at the joints and 24" o.c. in the field.
Alternate Method—1 Hour Incombustible U.L. No. 32
The face layer of 1/2" Firestop Type XXX or 1/2" Firestop Eternawall may be strip laminated without fasteners, except at the top and bottom track. Use 1 1/4" Type "S" screws spaced 8" o.c. at top and bottom track.
4. Tape and finish in the approved manner.

WOOD STUD PARTITION

STC 50

FIRE RATING

1 Hr. Combustible



SOUND TEST DATA

Test No.: BW-35ST
Dated: April 3, 1969
Conducted By: Geiger & Hamme, Inc.
Test Partition: Height: 9' Weight: 8.6 lbs./sq. ft.
Width: 14' 1/2"
Thickness: 5 3/4"
Sound Transmission Class 50

1. Nail 2" x 4" wood studs 16" o.c. to 2" x 4" wood plates at floor and ceiling.
2. Staple 1 1/2" thick economy Fiberglass batts to studs.
3. Apply single layer of 1/4" G-P/Bestwall Gypsum Sound Deadening Board vertically to both sides and secure with 4d. nails spaced 12" o.c. at studs and plates. Joints to be staggered on opposite sides.
4. Apply a single layer of 1/4" G-P/Bestwall Firestop Type X wallboard or Firestop Eternawall vertically to both sides over the 1/4" G-P/Bestwall Gypsum Sound Deadening Board by strip lamination 16" o.c. with G-P Laminating Compound. Compound is 2" inward from wallboard edge. Vertical joints of 1/4" should be offset 24" from 1/4" board joints. Nail top and bottom plates with 5d nails, 6" o.c.


SGP 0022895

4


ETERNAWALL™

VINYL SURFACED
GYPSUM WALLBOARD

Edge and Joint Treatment



BEVELED EDGE



SQUARE EDGE

Technical Data

1. Scope. This specification covers a high quality washable vinyl sheeting intended for use as wall-surfacing material.
2. Thickness. (Unsupported vinyl) .008".
3. Weight. 1.00 oz./sq. ft.
4. Composition. A vinyl compound of Polyvinyl Chloride resin combined with plasticizers, pigments and stabilizers to produce a durable, resistant surface.
5. Abrasion Resistance. (ASTM D1044—500 cycles, CS-17 wheels)
 - a. Maximum weight loss—50 milligrams;
 - b. Print wear off—no loss of print.
6. Accelerated Light Aging. (Fadeometer—ASTM 120 hours exposure). No appreciable discoloration or stiffening.
7. Washability. Good; no effect on the surface or stiffening when cleaned with mild or common household cleaners.
8. Panel. Thickness $\frac{1}{4}$ ", $\frac{3}{8}$ ", $\frac{1}{2}$ ", $\frac{5}{8}$ " Regular Gypsum Wallboard, $\frac{1}{2}$ " and $\frac{5}{8}$ " Firestop Gypsum Wallboard. Sizes: 4' x 7' to 4' x 16' in one foot increments. Special lengths on request. Special size (length and width) Eternawall partition board available on special order basis.
9. Fire Hazard Classification. $\frac{1}{2}$ " and $\frac{5}{8}$ " wallboard consisting of a gypsum core, surfaced on both sides with paper or with a vinyl facing on one side.

	Without Vinyl Facing	With Unsupported Vinyl Facing	With Supported (Fabric Backed) Vinyl Facing
Flame Spread	15	30	25
Fuel Contributed	15	10	10
Smoke Developed	0	60	40

SOURCE: Underwriters' Laboratories, Inc., Building Materials List, January, 1969.

Specifications

All vinyl surfaced gypsum wallboard indicated on the drawings shall be Georgia-Pacific Eternawall™ as manufactured by the Gypsum Division of Georgia-Pacific Corporation. The panel construction shall consist of an 8 mill unsupported vinyl sheeting of wall surfacing grade factory laminated to G-P Regular or Firestop™ Gypsum Wallboard. The long panel edges shall be (beveled, square) and completely wrapped with vinyl. The colors and patterns shall be as selected from the Standard (or Decorator) Line of Eternawall.

SGP 0022896

Application

Demountable wall systems are installed by using any of the appropriate or approved color-matched moldings. To laminate to existing wall surfaces, use G-P Laminating Compound and secure panels mechanically at top and bottom plates. Panels may be applied with adhesive directly to metal studs, wood framing or furring strips. For application directly to masonry walls, use G-P Grabit Masonry Adhesive.

GEORGIA-PACIFIC/BESTWALL F/7

WATER RESISTANT WALLBOARD

G-P/Bestwall Tile Backer Board is a water-resistant gypsum product with a light blue face paper, designed for use as a base for the adhesive application of ceramic, metal or plastic tile. The gypsum core consists of incombustible gypsum rock, combined with an emulsion giving high water resistance. This new G-P/Bestwall product is ideal for bathrooms, kitchens, powder rooms and all high moisture areas.

For fire rated partitions between bathrooms or interior areas subject to moisture use $\frac{5}{8}$ " Firestop Tile Backer proven by Underwriter's Laboratories in a 1-Hour assembly over wood studs.

The raw edges of Tile Backer Board (end joints, cut edges, cut-outs) are to be caulked with an approved waterproof non-hardening caulking compound. As an alternate to caulking, G-P can provide a special $2\frac{1}{2}$ " wide self-adhering vinyl tape to place over edges and cut-outs.

1. Scope of work

A. G-P/Bestwall Tile Backer Board shall be applied, as a base for (ceramic) (metal) (plastic) tile, to all wall areas where such tile serves as the finished decorative surface (and/or water barrier).

B. The contractor shall supply all tools, materials, and labor necessary and required to complete all work included in this section.

C. Adequate blocking for (tub) (prefabricated receptor) (sub pan) etc., is covered in section on Framing.

D. All materials shall be new, and used in strict accordance with the manufacturer's directions.

2. Materials

A. $\frac{1}{2}$ " thick G-P/Bestwall Tile Backer Board, manufactured by Georgia-Pacific Gypsum Division.

B. G-P/Bestwall Vinyl Tile Backer Board Tape, marketed by Georgia-Pacific Gypsum Division.

C. GWB #54 $1\frac{1}{4}$ " ring shank nails or equal.

D. Screws, if used as an alternate method of fastening, shall be 1" long drywall screws.

E. Temporary strip or shim of wood or a specially designed permanent metal section.

3. Workmanship

A. All framing members shall be rigidly fastened, plumb, and true.

B. Installation of (tub) (prefabricated receptor) (sub pan) shall have been completed prior to erection of Tile Backer Board.

C. Studs shall be furred out as necessary, around (tub) (prefabricated receptor) (sub pan) so that the face of the water resistant wallboard, when installed, shall be flush with the upper lip of the (tub) (prefabricated receptor) (sub pan).

D. Tile Backer Board shall be applied horizontally so as to minimize butt joints with paper bound edge along edge of (tub) (prefabricated receptor) (sub pan).

E. The contractor shall use a temporary strip or shim between the edge of Tile Backer Board and the lip of the (tub) (prefabricated receptor) (sub pan). When the temporary strip or shim is removed, a clearance of $\frac{1}{4}$ " shall exist between the edge of the Tile Backer Board and the lip of the (tub) (prefabricated receptor) (sub pan). A metal section especially designed for this purpose may be attached to the framing before the Tile Backer Board is erected.


F. Tile Backer Board shall be fastened to side walls with nails spaced 8" o.c. Where side walls are to be faced with ceramic tile thicker than $\frac{1}{4}$ ", nails shall be spaced 4" o.c.

G. Tile Backer Board shall be fastened to ceilings with nails spaced 7" o.c. (adhesive application of tile to wall-board ceilings is not recommended).


H. If adhesive nail-on application is used as an alternate method of fastening, the contractor shall use not less than 2 nails per board width per support.

I. Vinyl tape, if used, shall not be applied to side walls and ceilings above the tile line. Tile Backer Board above the tile line shall receive standard joint treatment. This area shall be primed and painted as other painted areas.







Partition Section Metal




Wall Furring Detail




A suggested alternate detail to be used where building movement is anticipated to the extent that the non load bearing partition will be loaded and relief is needed. There are other acceptable methods.




Door Details




Ceiling Furring Detail




Corner Detail



Elevation



A suggested relief joint for long runs of partitions to be provided at 40 ft. maximum centers.



Intersecting Wall

SGP 0022898



TECHNICAL DATA

GYPSUM WALLBOARD CONSTRUCTION WALLS AND COLUMNS

STUD SIZE	THICK- NESS	WEIGHT LB/SQ. FT.	WALL SURFACE	SOUND TRANSMISSION CHARACTERISTICS										SOUND TRANS. CHAR.				FIRE RESIST.		MODEL BUILDING CODE APPROVALS	
				INDIVIDUAL FREQUENCIES—CPS										STC	9 FREQ. AVG.	SPEECH PRIVACY RANGE	TEST REF.	RATING	TEST REF.		
				125	250	500	1000	2000	4000	1	2	3	4								5
NAILABLE STEEL STUDS (Loadbearing 3 5/8"—24" o.c.)																					
3 5/8"	4 1/4"	6.5	1/2" Bestwall Firestop, 1 layer each side	—	—	—	—	—	—	—	—	—	47	44	—	—	1 Hr.	T-209	ABC		
SCREW TYPE STEEL STUDS (Non-loadbearing 1 5/8"—2 1/2"—3 5/8"—24" o.c.)																					
1 5/8"	2 1/4"	5.2	1/2" Bestwall Firestop, one layer each side	25	29	35	35	40	41	44	43	33	36	44	35	36	—	TL-62-72	1 Hr.	T-2316	ABC
1 5/8"	2 1/4"	0.0	1/2" Bestwall Firestop, plus 1 1/2" fiber glass insulation in stud space	21	32	36	43	49	53	55	53	43	44	49	44	42	50	OR-64-81	1 Hr.	EST	—
1 5/8"	3 1/4"	8.4	1/2" Bestwall Firestop, 1 layer one side, 1 1/2" fiber glass insulation in stud space, 1 layer 1/4" Bestwall Firestop over 1" core board other side	30	38	43	49	51	54	55	54	51	50	53	52	47	52	OR-64-61	1 1/2 Hr.	EST	—
1 5/8"	3 1/4"	7.2	1/2" Bestwall Firestop, one layer, other side two layers, 1 1/2" fiber glass insulation in stud space	29	37	40	46	51	54	57	54	46	48	53	48	46	52	OR-64-80	1 1/2 Hr.	EST	—
2 1/4"	3 1/4"	—	1/2" Bestwall, one layer each side	14	23	24	30	34	40	47	50	48	38	41	35	33	42	OR-65-2	45 Min.	EST	—
2 1/4"	3 1/4"	4.3	1/2" Bestwall, Firestop, one layer each side, 2" fiber glass insulation in stud space	18	26	33	40	47	52	56	55	55	45	45	41	41	55	OR-66-5	1 Hr.	EST	—
2 1/4"	3 1/4"	—	1/2" Bestwall Firestop, one layer each side vinyl covered (Eternawall)	14	19	23	30	33	39	45	45	45	40	42	35	33	41	OR-64-65	1 Hr.	T-2898	AB—
2 1/4"	3 1/4"	—	1/2" Bestwall Firestop, one layer each side	24	23	28	34	40	44	49	49	40	39	45	39	—	—	OR-63-1	1 Hr.	T-2069	A—
2 1/4"	4"	6.3	1/2" Bestwall Firestop, one layer, other side two layers, plus 2" fiber glass insulation in stud space	25	33	40	46	52	57	60	60	59	52	52	48	47	57	OR-66-6	1 1/2 Hr.	EST	—
2 1/4"	4"	7.0	1/2" Bestwall Firestop, one layer laminated over 1/4" gypsum sound deadening board, both sides screw attached	28.8	29.1	35.8	38.9	45.6	49.4	52.1	57.5	61.4	60.5	57.2	45	44.3	54.4	BW-16-FT	1 Hr.	UL32	—
2 1/4"	4"	7.12	1/2" Bestwall Firestop, laminated one layer over 1/4" gypsum sound deadening board, screw attached, both sides, plus 2" fiber glass friction fit in stud space	33	32	42	48	54	53	54	59	63	62	59	50	48.7	57.5	BW-17-FT	1 Hr.	UL32	—
2 1/4"	4 1/4"	8.12	1/2" Bestwall Firestop, one layer laminated over 1/4" gypsum sound deadening board, both sides, screw attached, plus 2" fiber glass friction fit in stud space	32	39	44	48	55	55	57	60	63	62	60	54	50.2	58.7	BW-18-FT	1 Hr.	UL32	—
2 1/4"	4 1/4"	8.0	1/2" Bestwall Firestop, two layers each side (for sound—add 2" fiber glass insulation in stud space).	24	38	45	49	54	54	51	56	55	53	55	47	45	54.3	BW-12-FT	2 Hrs.	T-3218	ABC
2 1/4"	4 1/4"	7.5	1/2" Bestwall Firestop, one layer, other side— two layers	28.5	28	32	36.5	43	47.5	51	51.5	44	45	50	43	40	46	OR-63-2	1 1/2 Hr.	EST	—

WARRANTY:

The assemblies covered above have been developed with due regard to practical construction methods. However, since the Bestwall Gypsum Division does not have any prior knowledge of a specific building design and its construction or the methods of application used with their products, no warranty of performance is made. All of the test results have been obtained under laboratory testing conditions where controlled environment reduces variables to a minimum. In the field, such laboratory conditions are not always met, since many other variables are introduced. Laboratory results may exceed results of field tests, but the laboratory tests under controlled conditions are the only logical way to compare the performance of different assemblies. The Bestwall Gypsum Division of the Georgia-Pacific Corporation makes no warranty that the performance of assemblies in the field will have a performance equal to or better than that developed in the test.

SGP 0022899

STUD SIZE	THICK- NESS	WEIGHT LB/SQ. FT.	WALL SURFACE	SOUND TRANSMISSION CHARACTERISTICS						SOUND TRANS. CHAR.			FIRE RESIST.		MODEL BUILDING CODE APPROVALS	
				INDIVIDUAL FREQUENCIES—CPS						STC	9 FREQ. AVG.	SPEECH PRIVACY RANGE	TEST REF.	RATING		TEST REF.
				125	250	500	1000	2000	4000							

SCREW TYPE STEEL STUDS (Non-loadbearing 2½"–3⅝"–24" o.c.) Cont'd.

2½"	5"	10.4	¾" Bestwall Firestop, two layers, both sides	—	—	—	—	—	—	—	—	—	46	—	—	EST	2 Hrs.	T-2557	AB—		
3½"	4½"	6.0	¾" Bestwall Firestop, one layer each side	20.5	26	31	37	41.5	46	50	50.5	42	40	48	42	38	45	OR-63-11	1 Hr.	T-2016	ABC
3½"	5½"	8.0	¾" Bestwall Firestop, one layer, other side two layers	24	25	33	40	46	49	52	51	44	45	50	43	40	48	OR-64-32	1½ Hrs.	EST	—
3½"	5½"	8.0	¾" Bestwall Firestop, one layer, other side two layers, plus 3" fiber glass insulation in stud space	31	37	45	49	52	55	57	55	50	48	51	50	47	53	OR-64-51	1½ Hrs.	T-3126	AB—
3½"	5½"	5.75	¾" Bestwall Firestop, one layer, other side, one layer over ½" Bestwall sound dead- ening board	24	26	34	40	47	51	55	55	48	47	53	44	42	50	OR-65-10	1 Hr.	EST	—
3½"	5½"	—	¾" Bestwall Firestop, one layer over ½" Bestwall sound dead- ening board, both sides	28	32	39	46	52	56	57	60	55	55	59	49	47	56	OR-65-11	1 Hr.	EST	—
3½"	6½"	11.0	¾" Bestwall Firestop, two layers each side	28	29	36	44	48	52	55	53	47	51	55	47	44	51	OR-64-52	2 Hrs.	EST	—
3½"	6½"	11.1	¾" Bestwall Firestop, two layers, both sides, plus 1½" fiber glass insulation in stud space	36	41	49	51	53	55	56	55	50	52	55	52	50	54	OR-64-50	2 Hrs.	EST	—
3½"	6½"	10.4	¾" Bestwall Firestop, two layers, (face layer —Eternawall)	31	37	45	49	52	55	57	55	50	48	51	50	47.4	—	—	2 Hrs.	T-2406	ABC

SLIP JOINT AT CEILING (2½"–24" o.c.) (Non-loadbearing) — ½" x 12" Gypsum spacers fastened on Quarter points

2½"	3½"	4.3	¾" Bestwall Firestop, one layer each side, 2" fiber glass insulation in stud space	18	25	33	39	46	50	53	53	52	43	44	40	40	50	OR-66-7	1 Hr.	EST	—
2½"	3½"	3.8	¾" Bestwall, one layer each side	15	21	26	32	35	42	47	49	46	39	43	37	34	43	OR-65-1	45 Min.	EST	—

METAL STUD (or double row metal studs) Non-loadbearing, 1⅝"–24" o.c.

1½"	7½"	6.69	¾" Bestwall Firestop, laminated 1 layer over ¼" Gypsum Sound Deadening Board; both sides.	30	—	35	—	45	—	54	—	55	—	60	47	44.3	53	BW-33ST	1 Hr.	EST	—	A —
1½"	7½"	6.84	¾" Bestwall Firestop, laminated 1 layer over ¼" Gypsum Sound Deadening Board; both sides, 1½" insulation.	33	—	41	—	50	—	56	—	56	—	61	52	47.9	55	BW-34ST	1 Hr.	EST	—	A —

SEMI-SOLID GYPSUM PARTITIONS (Non-loadbearing 1" x 6"—2½" x 3"—¾" x 6" Laminated Gypsum Ribs—24" o.c.)

1" x 6"	BESTWALL 2½"	HUMMER 7.2	"B" ¾" Bestwall Firestop, one layer each side.	21	17	27	34	36	40	39	43	36	36	39	35	32	38.3	BW-8-FT	1 Hr.	UL 10	ABC
2½" x 3"	4½"	7.2	¾" Bestwall Firestop, one layer, other side, one layer screwed to resilient channels. Plus 2" fiber glass insul. in stud space.	28	39	43	47	50	54	58	57	53	53	57	51	48	54	OR-65-19	1 Hr.	EST	—
2½" x 3"	4½"	7.9	¾" Bestwall Firestop, one layer over ½" Bestwall S.D. Board—both sides.	28	36	43	46	50	54	58	59	58	57	59	51	48	56	OR-64-57	1 Hr.	T-3128	AB—
¾" x 6"	BESTWALL 2½"	HUMMER 7.8	"C" ¾" Bestwall, two layers each side.	23	23	31	36	36	38	39	39	36	36	41	37	34	37	TL-60-131	1 Hr.	T-1276	ABC

SOLID GYPSUM BOARD PARTITIONS (Non-loadbearing)

2"	8.1	½" Bestwall, one layer each side, 1" Coreboard	—	—	—	—	—	—	—	—	—	—	—	—	37	—	—	G.A.	2 Hrs.	G.A.	—
2"	8.1	½" Bestwall Firestop, one layer each side, 1" Coreboard	—	—	—	—	—	—	—	—	—	—	—	—	39	—	—	G.A.	2 Hrs.	G.A.	—
2½"	9.1	¾" Bestwall Firestop, one layer each side, 1" Coreboard	—	—	—	—	—	—	—	—	—	—	—	—	36	—	—	G.A.	2 Hrs.	EST	—

Gypsum Wallboard Construction, Walls and Columns (Cont.)

STUD SIZE	THICK- NESS	WEIGHT LB./SQ. FT.	WALL SURFACE	SOUND TRANSMISSION CHARACTERISTICS						SOUND TRANS. CHAR.			FIRE RESIST.		MODEL BUILDING CODE APPROVALS	
				INDIVIDUAL FREQUENCIES—CPS						STC	9 FREQ. AVG.	SPEECH PRIVACY RANGE	TEST REF.	RATING		TEST REF.
				125	250	500	1000	2000	4000							

DOUBLE SOLID GYPSUM BOARD PARTITIONS (Non-loadbearing)

4"	13.4	1/2" Bestwall Firestop, 2 layers each side, 1" Rib Coreboard	29.5	31	34.5	37	38	36.5	35	—	42	—	51.5	35	37	—	TR-57-42	2 Hrs.	U.L. 7	ABC
5"	13.4	1/2" Bestwall Firestop, 2 layers each side, 1" Rib Coreboard	32	34	37.5	39.5	39.5	38	38.5	—	46.5	—	54	—	40	—	TR-57-43	3 Hrs.	U.L. 5	ABC
6"	9.5	1/2" Bestwall over 1/2" Bestwall Firestop, each side, 1" Coreboard	—	—	—	—	—	—	—	—	—	—	—	—	—	—	OR-64-39	1 1/2 Hrs.	U.L.	—
6"	13	1/2" Bestwall over 1" Coreboard, each side of 3" air space	31	36	41	47	49	49	49	47	51	56	60	47	46	52	OR-64-39	2 Hrs.	T-2575	ABC

TRIPLE SOLID GYPSUM BOARD PARTITIONS (Non-loadbearing)

6"	17	1/2" Bestwall, 1 layer over 1" Coreboard both sides 3" air space with 1" Coreboard centered in air space	29	34	40	45	47	50	54	55	59	60	60	51	46	54	OR-64-58	3 Hrs.	EST	—
6"	17.2	1/2" Bestwall, 1 layer over 1" Coreboard each side of 3" air space with 1" Coreboard centered in air space and fiber glass insulation in space on 1 side	36	45	49	53	55	56	56	58	60	62	63	58	53	58	OR-64-59	3 Hrs.	EST	—

PARTITIONS, METAL FACED (Non-loadbearing)

ELWIN G. SMITH AND CO. INC.	1/2" Bestwall Firestop, four layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 12	—B—
WALCON CORP.	1/2" Bestwall Firestop, four layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 10	—B—
R. C. MAHON CO.	1/2" Bestwall Firestop, five layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 9	—B—
	1/2" Bestwall Firestop, four layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 5	—B—
	1/2" Bestwall Firestop, 2 layers, each side	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	3 Hrs.	U.L. 8	—B—
	1/2" Bestwall Firestop, five layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	3 Hrs.	U.L. 7	—B—
H. N. ROBERTSON CO.	1/2" Bestwall Firestop, 2 layers, each side	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 8	—B—
	1/2" Bestwall Firestop, four layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 25	—
	1/2" Bestwall Firestop, four layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 22	—
	1/2" Bestwall Firestop, four layers, 1/2" F/S, and one layer 1/4" F/S	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	3 Hrs.	U.L. 9	—

STEEL COLUMN FIREPROOFING

1/2" Bestwall, 2 layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	1 Hr.	G.A.	—
1/2" Bestwall, 3 layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	1 1/2 Hr.	G.A.	—
1/2" Bestwall Firestop, 1 layer	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	1 Hr.	EST.	AB—
1/2" Bestwall Firestop, 2 layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 8	ABC
1/2" Bestwall Firestop, 3 layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	3 Hrs.	U.L. 18	ABC
1/2" Bestwall Firestop, 4 layers	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	4 Hrs.	U.L. 26	AB—

PARTITIONS (Wood studs 2" x 4"—16" o.c. using 1/4" Gypsum Sound Deadening Board)

2"x4"	5 1/2"	7.96	1/2" Bestwall Firestop, one layer strip laminated over 1/4" Gypsum Sound Deadening Board, both sides	23	—	39	—	43	—	49	—	59	—	54	45	43.1	52.3	BW27-FT	1 Hr.	U.L. 30	A—
2"x4"	5 1/2"	8.3	1/2" Bestwall Firestop, 1 layer over 1/4" Gypsum Sound Deadening Board; both sides, laminated.	23	—	39	—	44	—	50	—	52	—	57	47	42.9	50	BW-28ST	1 Hr.	U.L. 30	A—
2"x4"	5 1/2"	8.7	1/2" Bestwall Firestop Type X, one layer strip laminated, over 1/4" Gypsum Sound Deadening Board, both sides, 1 1/2" insulation.	27	—	38	—	48	—	51	—	53	—	56	50	—	—	BW-35	1 Hr.	U.L.	—
2"x4"	7 1/4"	8.79	1/2" Bestwall Firestop, 1 layer over 1/4" Gypsum Sound Deadening Board; both sides laminated, staggered studs.	30	—	34	—	45	—	52	—	53	—	56	47	43.4	51	BW-29ST	1 Hr.	EST	A—
2"x4"	7 1/4"	8.92	1/2" Bestwall Firestop, 1 layer laminated over 1/4" Gypsum Sound Deadening Board, both sides, 1 1/2" insulation, staggered studs.	34	—	42	—	49	—	54	—	55	—	60	52	48	54	BW-30ST	1 Hr.	EST	A—
2"x4"	10 1/4"	9.14	1/2" Bestwall Firestop, 1 layer laminated over 1/4" Gypsum Sound Deadening Board; both sides double studs.	31	—	38	—	46	—	52	—	56	—	59	50	44.6	53	BW-31ST	1 Hr.	EST	A—
2"x4"	10 1/4"	9.29	1/2" Bestwall Firestop, 1 layer laminated over 1/4" Gypsum Sound Deadening Board; both sides, 1 1/2" insulation, double studs.	39	—	44	—	52	—	56	—	58	—	61	55	48.9	56	BW-32ST	1 Hr.	EST	A—

SGP 0022901

STUD SIZE	THICKNESS	WEIGHT LB/SQ. FT.	WALL SURFACE	SOUND TRANSMISSION CHARACTERISTICS							SOUND TRANS. CHAR.			FIRE RESIST.		MODEL BUILDING CODE APPROVALS					
				INDIVIDUAL FREQUENCIES—CPS							STC	9 FREQ. AVG.	SPEECH PRIVACY RANGE	TEST REF.	RATING		TEST REF.				
				125	250	500	1000	2000	4000	1								2	3	4	5
PARTITIONS (wood studs 2" x 4"—16" o.c. Loadbearing except when noted—"N")																					
2"x4"	4 1/2"	5.2	1/2" Bestwall, both sides	22	23	28	32	33	41	44	—	46	—	39	31	—	—	EST BS-234	25 Min.	EST	A B C
2"x4"	4 1/2"	5.9	1/2" Bestwall, both sides	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	A B C
2"x4"	4 1/2"	6.0	1/2" Bestwall, both sides with Mineral Wool in stud space	—	—	—	—	—	—	—	—	—	—	—	39	—	—	EST	1 Hr.	BMS-92	A B
2"x4"	4 1/2"	5.9	1/2" Bestwall Firestop, both sides	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
2"x4"	4 3/4"	7.0	1/2" Bestwall Firestop, both sides	22	16	29	31	33	38	41	41.5	36	36.5	45	34	32	38	OR-64-8	1 Hr.	U.L. 5	A B C
2"x4"	4 3/4"	7.0	1/2" Bestwall Firestop, tile backer board, both sides	22	16	27	31	33	38	41	41.5	36	36.5	45	34	32	38	OR-64-8	1 Hr.	U.L. 5	A B C
2"x4"	5 1/2"	8.2	1/2" Bestwall, 2 layers, both sides	27	24	31	35	40	42	46	—	53	—	48	—	38	—	BS-225	1 Hr.	G.A.	A —
2"x4"	5 1/2"	9.5	1/2" Bestwall Firestop, one layer, other side two layers	23.5	19.5	33	34.5	36	40	43	45	40	40	47	37	35	41	CR-64-11	1 1/2 Hrs.	EST	—
2"x4"	5 3/4"	6.3	1/2" Bestwall Firestop, 1 layer nailed one side 1 layer on resilient furring other side	29.5	28	33	41	45	48.5	52	52.5	44	41	51	44	41	48	OR-64-7	1 Hr.	T-3127	A B C
2"x4"	5 3/4"	6.4	1/2" Bestwall Firestop, 1 layer nailed one side 1 layer on resilient furring other side plus fiber glass insulation in stud space	33.5	35	43	50.5	51	54	55	55	54	47.5	53	50	48	53	OR-64-53	1 Hr.	T-3127	A B C
2"x4"	5 3/4"	9.9	1/2" Bestwall, 2 layers both sides	—	—	—	—	—	—	—	—	—	—	—	39	39	39	NBS	1 1/2 Hrs.	G.A.	A —
2"x4"	7 1/2"	11.0	1/2" Bestwall, 2 layers both sides, staggered studs	42	40	39	40	45	42	45	—	41	—	53	43	43	—	OR-00-0	1 1/2 Hrs.	—	—
2"x4"	5 1/2"	8.5	1/2" Bestwall Firestop, over 1/2" Bestwall Sound Deadening Board both sides	25	30	38	43	47	52	57	58	55	54	59	46	45	54	OR-64-73	1 Hr.	T-3006	A B C
2"x4"	8 1/2"	13.4	1/2" Bestwall Firestop, 2 layers each side staggered studs	41	41	41	43	46	48	49	—	41	—	54	45	45	—	BS-244	2 Hrs.	EST	—
2"x4"	6"	8.8	1/2" Bestwall Firestop, 2 layers one side, 1 layer on resilient furring other side	32.5	32	38	44.5	49	52.5	55	56.5	49	45	54	48	45	51	OR-64-15	1 1/2 Hrs.	EST	—
2"x4"	6 1/2"	12.0	1/2" Bestwall Firestop, 2 layers each side	26.5	22	36	37	42	43.5	48	49.5	45	44.5	51	41	39	46	OR-64-12	2 Hrs.	T-194	A B C
2"x4"	8 1/2"	12.7	1/2" Firestop, 2 layers each side, staggered studs	30	—	40	—	44	—	51	—	48	—	57	47	—	—	TL-69-210	2 Hrs.	UL	A B C
FIRE RETARDANT WOOD STUDS (2" x 4"—24" o.c. 2" x 3"—24" o.c.—Non-loadbearing)																					
2"x4"	4 1/2"		1/2" Bestwall Firestop, one layer each side	—	—	—	—	—	—	—	—	—	—	—	34	—	—	EST	1 Hr.	F.P. LA 13 Univ. of Calif.	A B —
2"x4"	1 3/4"		1/2" Bestwall Firestop, one layer each side	—	—	—	—	—	—	—	—	—	—	—	32	—	—	EST	1 Hr.	—	—
EXTERIOR WALLS (Wood Studs 2" x 4"—16" o.c. Loadbearing)																					
5"			1/2" Bestwall Firestop, (Interior) one layer 1/2" Gypsum Shtg., and wood siding or other (Exterior)	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	1 Hr.	T-99 BMS-191-192	—
5 1/2"			1/2" Bestwall Firestop, two layers (Interior) 1/2" Gypsum Shtg., 2' x 8' T&G and 4" Brick wall (Exterior)	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	2 Hrs.	U.L. 23	—

NOTE: This table is a summary only, based on tests at Underwriters' Laboratories, National Bureau of Standards, University of California, Ohio State University, Geiger and Hammes, Riverbank Laboratories and/or Ohio Research Corporation sponsored by the Bestwall Gypsum Division, Gypsum Association, or others. The fire rating, weight and sound characteristics are based on a combination of specific details as tested and published.

FIRE HAZARD CLASSIFICATION: Official Underwriters' Tests. 1/2" and 5/8" Bestwall Firestop, 10-15 (Labeled); 1/4", 1/2", and 3/8" Bestwall, 10-15 (Not Labeled). More complete listings and details are available.

Inconsistencies in test results are due to tests over a period of many years and variations in laboratory facilities.

1. STC under sound characteristics is Sound Transmission Class.

2. 9 Frequency Average, the average decibel loss using nine of the eleven frequencies 125 to 4000 CPS range (Minus—1400 and 2800 Freq.)

3. Speech Privacy Range, the average decibel loss using six frequencies—500 to 2800 CPS range.

4. Official Underwriters' Tests have proven joint finishing is not required for the rating in assemblies of Firestop.

5. Under "Model Building Code Approvals" (A) refers to International Conference of Building Officials; (B) refers to Southern Building Code Congress; (C) refers to Building Officials Conference of America. Additional approvals requested.

WARRANTY:

The assemblies covered above have been developed with due regard to practical construction methods. However, since the Bestwall Gypsum Division does not have any prior knowledge of a specific building design and its construction or the methods of application used with their products, no warranty of performance is made. All of the test results have been obtained under laboratory testing conditions where controlled environment reduces variables to a minimum. In the field, such laboratory conditions are not always met, since many other variables are introduced. Laboratory results may exceed results of field tests, but the laboratory tests under controlled conditions are the only logical way to compare the performance of different assemblies. The Bestwall Gypsum Division of the Georgia-Pacific Corporation makes no warranty that the performance of assemblies in the field will have a performance equal to or better than that developed in the test.

SGP 0022902

Another system of drywall construction consists of the absence of wood or metal studs, either of which has its particular fire resistance deficiency value. In the following four systems (partially explained below) the common factor in each is that they are all constructed (except for floor ceiling runners) entirely of some form of gypsum incombustible material.

2" Solid Laminated—(Non-Load Bearing)—A 1" gypsum core board with a ½" gypsum laminated to each side; no air space at all, a 2" solid wall. Has a 2 hour fire rating, economical to buy and construct, a 35 decibel STC, creates smooth monolithic walls and creates extra usable floor space.

Materials: All gypsum wallboards, metal runners and accessories, laminating compound and joint system products used shall be furnished by the G-P/Bestwall Gypsum Division. Gypsum wallboard ½" thick Regular or Firestop, 4' wide x ceiling height, tapered edge, 1" coreboard 2' wide x ceiling height (homogenous or laminated) T&G edge.

Floor and Ceiling Runners: 1" x 1½" wood runner or 1" x 1½" roll formed 24 gauge galvanized sheet steel "L" or "U" shaped runner.

Fasteners: Nails 1½" long finishing nails. Screws 1" or 1¼" long G-P/Bestwall Type "S" drywall screws, 1¼" or 1¾" Type "G" drywall screws.


Application: Ceiling and floor track shall be aligned and anchored securely with suitable fasteners at a maximum of 24" o.c. Position 1" G-P/Bestwall coreboard (vertically) into ceiling and floor track fasten 24" o.c. and fasten with 1¼" long Type "S" Drywall screw. Apply G-P/Bestwall Laminating Compound to both sides of the 1" coreboard or the backs of the face wallboards. Use either a comb type spreader, or a mechanical tool designed for applying laminating compound. Notches should be ⅜" deep x ⅜" wide and spaced ¾" o.c. Position the face layers of wallboard and fasten along vertical edges and down middle of 4' wide board. Fasten with 1¼" Type "G" Drywall screws spaced at not over 24" o.c. in field—8" o.c. at top and bottom runner, maintain ⅜" space from edges and end of panel Drive screws slightly below the face without breaking face paper. Vertical joints of face boards shall be staggered a minimum of 6" from the vertical joints of coreboard. Vertical joints of the face boards shall be staggered from the vertical joints on the opposite side of the wall. Where walls are erected under a concrete floor slab, a ½" slip joint is recommended between the slab and the top edge of the 1" coreboard and the top edge of the face boards to allow for building movements (see detail).

NOTE: Before attaching metal runners at ceiling, floor and intersection of walls at columns, a bead of caulking should be applied in back of the metal runners for better resistance to sound transmission.

Joints: All joints should be taped and finished with G-P/Bestwall Bedding and Topping Compound. Nail or screw heads should be finished with bedding and topping compound. Exterior angles are covered with G-P/Bestwall Metal Corner Bead and finished with joint compound. The top edge of Wallboard at the ceiling angle adjacent to a concrete floor slab shall be finished with flat tape and joint compound or a G-P/Bestwall Metal Casing Bead over top edge of the face boards (see detail).


NOTE: This assembly with one layer ½" G-P/Bestwall Regular Gypsum Wallboard each side has a 2-hour fire resistive rating and a 9 FREQ. Av. of 37 db; for additional fire resistive ratings and sound transmission characteristics, see Page F/11.

2" SOLID LAMINATED GYPSUM WALLBOARD



SGP 0022903

2 1/4" SEMI-SOLID LAMINATED GYPSUM WALLBOARD



2 1/4" Semi-Solid Laminated—(Non-Load Bearing)—A center vertical rib (or stud) composed of 2 layers of gypsum laminated, (1" x 6" rib, 24 o.c.) is the base upon which 5/8" gypsum wallboards are laminated to each side. This leaves intermittent 1" dead spaces for wiring. Has a 1 hour fire rating, simplicity of installation saves money, a 30 decibel STC, creates smooth walls and provides extra floor space.

Materials: All gypsum wallboards, gypsum ribs, metal runners and accessories, laminating compound, joint system products used shall be furnished by the G-P/Bestwall Gypsum Division. Gypsum wallboard 1/2" or 5/8" thick Regular or Firestop 4' wide x ceiling height tapered edge-gypsum ribs consist of two layers of 1/2" gypsum wallboard, factory laminated 1" thick x 6" wide—other rib thicknesses available as detailed by partition thickness. Gypsum ribs may be cut 1/2" or 5" short of ceiling height.

Floor and Ceiling Runners: 1" x 5/8" wood runner or 1" x 1 1/2" roll formed 24 gauge galvanized sheet steel "L" and "U" shaped runners.

Fasteners: Nails—1 1/2" long finishing nails. Screws—1" or 1 1/4" long Type "S" Drywall screws—1 1/2" or 1 5/8" long Type "G" Drywall Screws.

Installation: Ceiling and floor runners shall be aligned and anchored securely with suitable fasteners at a maximum of 24" o.c. Position gypsum ribs into the ceiling and floor runners and laminate one layer of 5/8" G-P/Bestwall Firestop both sides of the assembly and fasten. Fasten with 1 5/8" Type "G" Drywall screws spaced 12" o.c. in field and 8" o.c. at top and bottom runner. Drive screws slightly below the surface without breaking the face paper and maintain 3/8" space from vertical edges and ends of panel. Vertical joints of the face boards are centered over the gypsum ribs, stagger the vertical joints from vertical joints of the opposite of the wall 24" o.c. Where walls are erected under a concrete floor slab, a 1/2" slip joint is recommended between the slab and the top edge of the gypsum rib and face boards to allow for building movement (see detail).

NOTE: Before attaching metal runners at ceiling, floor and intersection of walls at columns, a bead of caulking should be applied in back of the metal runners for better resistance to sound transmission.

Joints: All joints should be taped and finished with G-P/Bestwall Bedding and Topping Compound. Screw heads should be finished with bedding and topping compound. Exterior angles are covered with G-P/Bestwall Metal Corner Bead and finished with joint compound. The top edge of wallboard at the ceiling angle adjacent to a concrete floor slab shall be finished with flat tape and joint compound or a G-P/Bestwall Metal Casing Bead over top edge of the face boards. (See detail).

NOTE: 1/2" thick face board may be used for a 2" thick partition. Other depth ribs may be used for thicker partitions.

NOTE: When gypsum ribs cut 5" short of ceiling height are used, position and fasten one face layer gypsum wallboard, position 1" x 6" wide gypsum rib, and apply laminating compound and fasten with 1 1/2" long G-P/Bestwall Type "G" Drywall Screws.

NOTE: This assembly with one layer 5/8" G-P/Bestwall Firestop Gypsum Wallboard each side has a 1-hour fire resistive rating and an STC of 35. For additional fire resistive ratings and sound transmission characteristics, see Page F/11.

OTHER LAMINATED SYSTEMS

Double Solid Laminated—(Non-Load Bearing)—Consists of laminating 1/2" gypsum wallboard to a 1" tongue and groove coreboard homogenous or laminated on each side of a 3" air space. There is absolutely no connection over the air space except at the jambs. Has a 2 hour fire rating, greater strength than standard frame or thin solid wall, a 47 decibel STC and smooth wall surface.

Triple Solid Laminated—(Non-Load Bearing)—The center piece is a 1" gypsum core panel running the height and length of wall, on one side of which is dead space the other side is filled with fiberglass insulation. Outer section of wall (on both sides) is a 1/2" wallboard laminated to 1" coreboard (this gives a 1 1/2" wall on both sides of center section). This gives a three hour fire rating, a 57 decibel STC and smooth monolithic walls.

There are many different kinds of construction systems and all are based on the requirements of your particular building installation. Basically, the main considerations are usually: **Fire Resistance, Sound Transmission, Relative Strength of the Installation, Dimensional Restrictions** and lastly **Economy**.

GP/Bestwall has many different materials which can be used individually or collectively. The following pages will give you a brief selection of systems and their advantages. However, no matter which system is used there are some very basic installations considerations to keep in mind.

After the wall and floor and ceiling constructions have been selected, it is important that they be installed properly. The following precautions should be taken during installation to avoid situations or conditions which will detract from the sound control properties of the assembly:


Avoid connecting plenum chambers, ducts, vents, etc. These permit the unrestricted flow of sound. Corrective measures are to make partitions full height, and use ducts lined with absorbent material.

Materials: All gypsum wallboards, metal runners and accessories, joint system products used, shall be G-P/Bestwall Gypsum Wallboard $\frac{3}{8}$ ", $\frac{1}{2}$ " or $\frac{5}{8}$ " thick Regular or Firestop, 4' wide x ceiling height for vertical application or up to 16' long for horizontal application, tapered edge.

Framing: Prior to the gypsum board application, all framing members should be true and firmly nailed in a plane surface. Provide double studs at all corners. Both inside and outside intersections are formed by extending one edge of a panel over the other edge in a flush position and covering with tape and joint treatment. In single ply installation, all ends and joints of gypsum wallboard shall occur over framing members, except that this is not required for treated joints at right angles to framing members.

Application: Gypsum wallboard may be applied horizontally or vertically to 2" x 4" wood studs with nails or screws. (Alternate method-stud adhesive may be applied to studs before applying gypsum wallboard.) The gypsum wallboard shall be attached with GWB-54 annular ring nails $\frac{1}{4}$ " head, .098" Dia. ASTM-C380—1 $\frac{1}{4}$ "-1 $\frac{3}{8}$ " long or with 1 $\frac{1}{4}$ " long G-P/Bestwall Type "W" dry-wall screws. 1" long G-P/Bestwall type "S" Drywall screws.

WOOD STUD GYPSUM WALLBOARD PARTITION



SINGLE PLY GYPSUM WALLBOARD MAXIMUM FRAMING SPACING

Wallboard Thickness	Application
$\frac{3}{8}$ " sidewalls.....	Horizontal or Vertical 16" o.c.
$\frac{1}{2}$ " sidewalls.....	Horizontal or Vertical 24" o.c.
$\frac{5}{8}$ " sidewalls.....	Horizontal or Vertical 24" o.c.

NAILING OR SCREW SPACING FOR SINGLE-PLY GYPSUM WALLBOARD

(Framing 16" o.c.)


Wallboard Thickness	Single Nailing	Double Nailing
$\frac{3}{8}$ " sidewalls.....	8" o.c. Max.....	12" o.c. Max.
$\frac{1}{2}$ " sidewalls.....	8" o.c. Max.....	12" o.c. Max.
$\frac{5}{8}$ " sidewalls.....	8" o.c. Max.....	12" o.c. Max.

Framing 16" o.c.

Framing 24" o.c.

Wallboard Thickness	Screw Spacing	Screw Spacing
$\frac{3}{8}$ " sidewalls.....	16" o.c. Max.....	—
$\frac{1}{2}$ " sidewalls.....	16" o.c. Max.....	12" o.c. Max.
$\frac{5}{8}$ " sidewalls.....	16" o.c. Max.....	12" o.c. Max.

NOTE: Nails or screws should be driven not less than $\frac{3}{8}$ " from edges or ends of panels. While fasteners are being driven, the wallboard shall be held in firm contact with the underlying supports. Preferably, application of fasteners should proceed from the central portion of the wallboard to the ends and edge. Dimple nails or screws without breaking the face paper. **Joints:** All joints should be taped and finished with tape and joint compound, nail or screw heads should be finished with bedding and topping compound. Exterior angles are covered with G-P/Bestwall Metal Casing Beads and finished with joint compound.



SGP 0022905

CEILING AND FLOOR ASSEMBLIES

TECHNICAL DATA-FIRE RATINGS WITH FIREPROOF GYPSUM WALLBOARD

WEIGHT LB./SQ. FT.	SURFACE	SOUND RATING RATING TEST REF.	FIRE RESISTANCE RATING TEST REF.	MODEL BUILDING CODE APPROVAL (A)
FLOOR AND CEILING: Wood Joists 16" o.c. finished floor on rough sub-floor, except as noted.				
—	½" Bestwall, 1 layer	—	15 min.	A B C
11.4	½" Bestwall, 1 layer	—	25 min.	A B C
11.4	½" Bestwall Firestop, 1 layer	—	45 min.	A B
12.0	½" Bestwall Firestop, 1 layer	STC 38/INR —16 (Est.)	1 hr.	A B
16.0	½" Bestwall Firestop, 1 layer nailed; 2nd layer ¾" Firestop applied to resilient furring channel 24" o.c. between layers	—	2 hr.	A B C
13.0	½" Bestwall Firestop, 1 layer nailed	—	1 hr.	A B C
13.0	½" Bestwall Firestop applied to resilient metal furring 24" o.c.	STC 47 TL64-155	1 hr.	A B C
—	¾" Bestwall, 2 layers	—	30 min.	— — —
—	½" Bestwall, 2 layers	—	1 hr.	— — —
—	½" Bestwall Firestop, 1 layer, laminated and nailed to ¼" Bestwall Gypsum Sound Deadening Board, with floor of ¾" CD plywood, ½" particleboard underlayment, carpet and pad	STC 41 INR+25 BW-2MT	1 hr.	A
—	¾" Bestwall Firestop, 1 layer laminated and nailed to ¼" Bestwall Gypsum Sound Deadening Board with floor of ¾" CD plywood, ½" particleboard underlayment, carpet and pad	STC 42 INR+25 (Est.)	1 hr.	A B C
PREFABRICATED FLOOR PANELS spaced 12" o.c. — Combustible				
6.5	½" Bestwall Firestop, one layer over ½" sound deadening board (direct attached)	—	1 hr.	A — —
2" CONCRETE FLOOR ON METAL LATH over Steel Bar Joists 24" o.c. — Incombustible				
34.2	¾" Bestwall Firestop nailed or screwed to metal furring 16" o.c.	—	1 hr.	A B C
34.2	¾" Bestwall Firestop Backer, nailed or screwed to metal furring 16" o.c.	—	1 hr.	A B C
32.0	¾" Bestwall Firestop, 1 layer, metal furring 24" o.c.	—	1 hr.	A B C
33.9	½" Bestwall Firestop, metal furring 24" o.c.	—	1½ hr.	A B C
34.1	¾" Bestwall Firestop, metal furring 24" o.c.	—	1¼ hr.	A B C
36.4	¾" Bestwall Firestop, metal furring 24" o.c.	—	2 hr.	A — —
—	¾" Bestwall Firestop metal deck	—	2 hr.	U.L. File R4024-12
2½" CONCRETE FLOOR ON METAL LATH over Steel Bar Joists, 24" o.c. — Incombustible				
38.5	½" Bestwall Firestop, metal furring 24" o.c.	—	2 hr.	A B C
39.3	¾" Bestwall Firestop, metal furring 24" o.c.	—	2 hr.	A B C
38.0	¾" Bestwall Firestop 2 x 2 ft. lay-in, metal grid	—	2 hr.	A B C
BEAM PROTECTION				
—	¾" Bestwall Firestop, two layers	—	2 hr.	U.L. No. 254, 255 — — —

SOUND CHARACTERISTICS—References: Geiger and Hamme, Inc.; Riverbank Labs.

(A) UNDER MODEL BUILDING CODE APPROVALS.

A—Refers to International Conference of Building Officials.

B—Refers to Southern Building Code Congress.

C—Refers to Building Officials Conference of America.

Additional Approvals Requested.

NOTE 1. This table is a summary only, based on tests at Underwriters' Laboratories, National Bureau of Standards, University of California, Ohio State University, sponsored by the G-P/Bestwall Gypsum Division, Gypsum Association, or others. The fire rating, weights and sound characteristics are based on a combination of specific details as tested and published.

COMBUSTIBLE ASSEMBLIES

NOTE 2. For all 45 minute and 1 hour ratings ¾" structural interior plywood underlayment grade, over building paper, over ½" structural interior plywood with exterior glue C-D grade may be used over the wood joists with ceilings as detailed.

INCOMBUSTIBLE ASSEMBLIES

NOTE 3. Ceilings for all 1 hour, 1½ hour and 2 hour incombustible floor and ceiling construction assemblies with 2" or 2½" concrete floor on metal lath over steel bar joints, unless otherwise specified, may be direct attached or suspended.

WARRANTY:

The assemblies covered have been developed with due regard to practical construction methods. However, since the G-P/Bestwall Gypsum Division does not have any prior knowledge of a specific building design and its construction or the methods of application used with their products, no warranty of performance is made. All of the test results have been obtained under laboratory testing conditions where controlled environment reduces variables to a minimum. In the field, such laboratory conditions are not always met, since many other variables are introduced. Laboratory results may exceed results of field tests, but the laboratory tests under controlled conditions are the only logical way to compare the performance of different assemblies. The Bestwall Gypsum Division of the G-P Corporation makes no warranty that the performance of assemblies in the field will have a performance equal to or better than that developed in the test.

SGP 0022906

Firestop® Gypsum Backer

LENGTH—6' to 16'. THICKNESS—⅝", ½".

WIDTH—2', 4'. EDGES—Tongue-and-Groove; Square.

G-P/Bestwall Firestop Gypsum Backer, with glass fiber reinforcement is used as a backing for decorative surface treatments of acoustical plasters, tile, plywood and various veneers. A single layer application of G-P/Bestwall Firestop Gypsum Backer on both sides of wood or steel framing, enables load bearing or non-load bearing walls, floors and ceiling assemblies to resist temperatures rising to 1700° F. in a standard time temperature curve for one hour.

Official Sound Transmission Tests of various assemblies allow possible floor and ceiling assemblies with superior ratings Sound Transmission.

G-P/Bestwall Firestop is listed by Underwriters and carries the UL Label for 45 minutes, 1, 2, and 3 hour Fire Resistance in various Designs and with a Fire Hazard Classification of 10-15.

GEORGIA-PACIFIC/BESTWALL F/17

FIRESTOP® ON RESILIENT METAL FURRING

ONE HOUR FIRE RATING TEST DATA

Test No.: TL 64-155

Dated: February 7, 1964

CONDUCTED BY: Riverbank Acoustical Laboratories.

TEST PARTITION—

WEIGHT 13.0 lbs./sq. ft.

Sound Transmission Class—47 db.

9 Frequency Average—44 db.

Speech Interference Zone—49 db.

FIRE RESISTANCE TEST DATA

Test No.: U.L. Design No. 33

Dated: January 24, 1964



Conducted By: Underwriters' Laboratories Inc.

MATERIALS USED


1. 2" x 10" wood joists.
2. Rosin building paper.
3. 1" x 6" tongue and groove subflooring.
4. 1" x 4" tongue and groove finished flooring.
5. Donn DG-8 Resilient Channels.
6. ½" G-P/Bestwall Firestop Gypsum Wallboard.
7. 1" G-P/Bestwall Type S Drywall Screws and 8d nails.

APPLICATION DETAILS

1. Fasten resilient channels on the under side of wood joists 16" o.c., perpendicular to joists and spaced 24" o.c. with an additional short section at the wallboard joint.
2. Attach ½" G-P/Bestwall Firestop with the long panel edge at right angle to the resilient channels, with end joints staggered.
3. Taped joints not required to obtain fire rating.




HORIZONTAL SECTION, FRONT VIEW



HORIZONTAL SECTION, SIDE VIEW

SGP 0022907


5/8" FIRESTOP®- 2 HR. RATING -INCOMBUSTIBLE



UL Design 259 - 2 Hr. (with 2" concrete)

G-P/Bestwall produces lighter weight board and better fire resistance! New 5/8" Firestop Gypsum Wallboard reinforced with glass fibers covers all ratings listed by Underwriters' Laboratories for the 5/8" thick material. This means that G-P/Bestwall 5/8" fire-rated board can be used in all kinds of wall, floor and ceiling assemblies.

The 10% reduction in weight can result in savings in labor and materials in multiple story construction. See your nearest G-P/Bestwall distribution center or write G-P/Bestwall Gypsum Division for further information.




COLUMN FIREPROOFING

Fireproofing with G-P/Bestwall Firestop Gypsum Wallboard provides a fast, efficient and economical method of protecting steel columns. Fire resistant assemblies of two, three and four hours are obtainable depending upon the number of layers of 5/8" or 1/2" G-P/Bestwall Firestop used. These layers are held in place by a combination of screws and metal studs. The two, three and four hour fire rated assemblies of Firestop have passed Official Fire Tests conducted by the Underwriters' Laboratories.


Fire Resistance—4 hour fire resistive protection for steel columns can be obtained with four layers of 5/8" G-P/Bestwall Firestop Type X. 3 hour fire resistive protection can be obtained with three layers and 2 hour fire resistive protection can be obtained with two layers of 5/8" Firestop Type X. Where necessary 1 hour of fire protection can be obtained with two layers of 1/2" G-P/Bestwall Gypsum Wallboard and 1 1/2 hour protection with 3 layers of G-P/Bestwall Gypsum Wallboard.

Lighter—As compared to other types of fireproofing, a dead load saving of from 50 to 75% can be realized with G-P/Bestwall Firestop Column Fireproofing.

Speed of Erection—G-P/Bestwall Firestop Gypsum Wallboard can be installed quickly and easily when used for column fireproofing following G-P/Bestwall details. Minimum amount of the wire and adhesives are used.



ILLUSTRATION—THREE-HOUR fire rated steel column assembly with 5/8" G-P/Bestwall Firestop.



ILLUSTRATION—TWO-HOUR fire rated steel column assembly with 5/8" G-P/Bestwall Firestop.

SGP 0022908

SALES OFFICES

Plywood

CALIFORNIA
Los Angeles
7240 Crider Ave.
Pico Rivera
GEORGIA
Atlanta
125 Otley Drive, N.E.
Savannah
P.O. Box 367
ILLINOIS
Chicago
Franklin Park
Waveland and Carnation
NEW JERSEY
Clifton
400 Allwood Road
OREGON
Portland
Commonwealth Bldg.
TEXAS
Dallas
1800 John Connally Dr.
Carrollton

WASHINGTON

Seattle
410 Terry Ave. North
Redwood Lumber
CALIFORNIA
Headquarters: Samoa
San Francisco
601 California St.
Los Angeles
7240 Crider Ave.
Pico Rivera
GEORGIA
Augusta
Southern Finance Bldg.
ILLINOIS
Franklin Park
3815 N. Carnation St.
NEW YORK
New York
375 Park Avenue
OREGON
Portland
Commonwealth Bldg.

Western Lumber

CALIFORNIA
San Francisco
601 California St.
Los Angeles
7240 Crider Ave.
Pico Rivera
GEORGIA
Augusta
Southern Finance Bldg.
OREGON
Portland
Commonwealth Bldg.
Southern Lumber
ARKANSAS
Crossett
CALIFORNIA
City of Industry
14750 Nelson Ave.

GEORGIA

Augusta
Southern Finance Bldg.
Gypsum Building Products
GEORGIA
Atlanta
P.O. Box 13505
Station K
NORTH CAROLINA
Charlotte
3300 Parkside Dr.
ILLINOIS
Chicago
P.O. Box 309
3815 N. Carnation St.
Franklin Park
OHIO
Cleveland
19100 Holland Rd.

TEXAS

Dallas
1800 John Connally Dr.
Carrollton
CALIFORNIA
Los Angeles
7240 Crider Ave.
Pico Rivera
San Francisco
800 Grayson St.
Berkeley
WASHINGTON
Seattle
410 Terry Ave., N.
WASHINGTON, D.C.
Washington, D.C.
3360 New York Ave., N.E.
DELAWARE
Wilmington
Wilmington Marine
Terminal
P.O. Box 310

DISTRIBUTION CENTERS

ALABAMA
Birmingham
3400 Ball St.
Mobile
3451 Georgia-Pacific Ave.
Beltline Hwy.
Montgomery
4542 Baldwin Ave.
ARIZONA
Phoenix
4801 West Colter St.
ARKANSAS
Little Rock
3101 Dugan St.
CALIFORNIA
Anaheim
519 E. Katella Ave.
Berkeley
800 Grayson St.
City of Industry
Georgia-Pacific
Board Fabricators
Hardwood Lumber Center
14750 Nelson Ave.
Fresno
5286 E. Home Ave.
Los Angeles
7240 Crider Ave.
Pico Rivera
Riverside
1350 Citrus St.
Sacramento
2951 Orange Grove Ave.
North Highlands
Salinas
1031 Industrial Ave.
San Diego
2200 Haffy St.
National City
San Fernando
7891 Deering Ave.
Canoga Park
San Jose
660 East Gish Rd.
COLORADO
Denver
1505 W. Third Ave.
CONNECTICUT
Wallingford
805 N. Colony St.
FLORIDA
Jacksonville
1333 Haines St.
Miami
3201 N.W. 110th St.
Orlando
2721 Regent Ave.
Tampa
3701 E. Columbus Dr.
GEORGIA
Albany
1013 Worth St.
Atlanta
125 Otley Drive, N.E.
Augusta
1153 Gordon Highway

Savannah
440 Magazine Ave.
IDAHO
Boise
1675 Commerce Ave.
IOWA
Des Moines
5631 Northeast 17th St.
ILLINOIS
Chicago
11909 Avenue "O"
Franklin Park
10450 Waveland Ave.
Peoria
206 West Camp St.
INDIANA
Elkhart
225 Collins Rd.
Evansville
520 N. Congress Ave.
Indianapolis
310 So. Kitley Ave.
KENTUCKY
Louisville
4820 Allmond Ave.
LOUISIANA
Lafayette
Evangeline Thruway, S.
New Orleans
900 S. Galvez St.
Shreveport
Mansfield Road at
Valley View
P.O. Box 8267
MAINE
Portland
508 Warren Ave.
MARYLAND
Baltimore
6813 Quad Ave.
Easton
Cherry St. & Penn. Ave.
MASSACHUSETTS
Boston
60 Kendrick St.
Needham Heights
MICHIGAN
Grand Rapids
825 Buchanan Ave., S.W.
Detroit
126 East Hudson St.
Royal Oak
MINNESOTA
Minneapolis
3101 East Hennepin Ave.
MISSISSIPPI
Jackson
555 Gulf Line Rd.
MISSOURI
St. Louis
6025 Byassee Dr.
Hazelwood
Kansas City
1445 Taney St.
N. Kansas City

MONTANA
Billings
Northern Pacific
Industrial Sites
Great Falls
901 River Drive South
NEBRASKA
Lincoln
545 "L" St.
NEW HAMPSHIRE
Manchester
300 Gay St.
NEW JERSEY
Clifton
400 Allwood Rd.
NEW MEXICO
Albuquerque
4021 Edith Blvd., N.E.
NEW YORK
Albany
Brown & Industrial Roads
Buffalo
2585 Walden Ave.
Rochester
1460 E. Henrietta Rd.
Long Island
175 Underhill Blvd.
Syosset
Syracuse
Midler Park Dr.
Syracuse
Yonkers
75 Tuckahoe Rd.
NORTH CAROLINA
Charlotte
3300 Parkside Rd.
Greensboro
2704 Patterson Dr.
OHIO
Akron
2644 Gilchrist Rd.
Cincinnati
5402 Vine St.
Cleveland
19100 Holland Rd.
Columbus
2100 Refugee Rd.
Dayton
4395 Springfield St.
Toledo
2815 Hill Ave.
OKLAHOMA
Oklahoma City
5519 N.W. Fourth St.
Tulsa
8531 East 44th
OREGON
Eugene
885 McKinley St.
Portland
330 S.E. Division Pl.
PENNSYLVANIA
Lancaster
549 W. Roseville Rd.

Pittsburgh
Hunker Rd. & Rt. 119
New Stanton
Philadelphia
801 First Ave.
King of Prussia
St. Clair
P.O. Box 37
RHODE ISLAND
Providence
170 Jefferson Blvd.
Warwick
SOUTH CAROLINA
Columbia
Corner Brookwood Dr. &
Duval St.
Greenville
Haywood Rd.
TENNESSEE
Bristol
100 Paty Industrial Blvd.
Chattanooga
201 East 28th St.
Knoxville
1301 Mitchell St., N.E.
Memphis
2057 Kellogg Ave.
Nashville
331 28th Avenue N.
TEXAS
Dallas
1800 John Connally Dr.
Carrollton
El Paso
1201 Airway Blvd.
Fort Worth
400 East Vickery Blvd.
Houston
4715 Calhoun Rd.
Lubbock
702 E. 44th St.
San Antonio
535 No. W. W. White Rd.
UTAH
Salt Lake City
2875 South Second, West
VIRGINIA
Norfolk
3587 Argonne Ave.
Richmond
Corner Dabney &
Bethlehem Rds.
WASHINGTON
Seattle
410 Terry Ave. North
Spokane
4320 E. Trent Ave.
Tacoma
2302 Ross Way
Washington, D.C.
3360 New York Ave., N.E.
WISCONSIN
Milwaukee
5059 N. 119th St.



SGP 0022909