

Paint Research
July, 1961

-16-

#97 - SWP 471

REDACTED

A series of panels numbered 16014-17 were prepared during the month for exposure at Chicago, Coffeyville and Miami. This is a long range series numbering 160 panels in all for comparisons of lead-in-oil versus SWP two coat and three coat systems. The woods used were cedar and Douglas Fir bevel siding. The panels are prepared in 5 sets of duplicates for each paint so that one pair of each can be retired at the end of each year. In this way we will obtain a valuable set of comparisons of the performance of lead-in-oil versus ready mixed paint at 1, 2, 3, 4 and 5 years for exhibition purposes. They can be used to combat promotion of lead-in-oil.

REDACTED

N39113