SINCE 1875

O'BRIEN'S

CISCO

No. 102

OUTSIDE WHITE

MADE BY THE O'BRIEN CORPORATION · SOUTH BEND, IND. · BALTIMORE, MD. · OKLAHOMA CITY, OKLA.

49 TOC 001246

3/22/56

REGISTERED
No. 55138
DATE 2/24/56

THE O'BRIEN CORPORATION

SOUTH BEND	INDIANA
BALTIMORE	MARYLAND
OKLAHOMA CITY	OKLAHOMA
SAN FRANCISCO	CALIFORNIA

ONE GALLON

2069-4

St.

DIRECTIONS

Surface must be clean and free from grease or oil and perfectly dry. Rough spots should be sanded thoroughly. Shellac knotty or pitchy spots before painting.

If possible, pour off the thinners into another container and add back gradually while stirring vigorously. If paint is too heavy add turpentine for inside use. For outside use add turpentine for first coat, Linseed Oil for second coat.

Brush the paint out well. Allow 24 hours drying time between coats.

Average Coverage 400-500 square feet per gallon.

Pigment	62.05%
Zinc Oxide	26.00%
Basic Lead Sulphate	31.00%
Titanium Dioxide	15.30%
Magnesium Silicate	27.70%
	100.00%
Vehicle	37.95%
Raw Linseed Oil	62.49%
Heat Treated Linseed Oil	16.02%
Mineral Spirits & Driers	21.49%
	100.00%

49 TOC 001247