Mr. Paul Logue - 2 nam:

January 12, 1934

AROCLOR-SULPHUR IMPREGNATION

Supplementing the information previously sent you on the subject of using Aroclor as an introfier for sulphur in impregnation, our laboratory has released the following information.

The initial freezing point of a 90% sulphur and 10% Aroclor 4465 mixture is 107.5° C.

The viscosity at 125° C. was reported as 47 seconds Saybolt Universal.

T. S. Foley

DSW 312172

STLCOPCB4072158