MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 17908 LOT 33941

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1850	1	T—	205	
1840	1	T—	259	
	STUMP			

TOTAL NET WT. 3690 PKG. N—CODE —

PROD. SPVR. DATE WHSE. OPER.

JP 1/28/80

CG 03 CODE KY-908-D PKG. ____

→ 11/25 ~~JAN 25~~ 33941

EST. WGT. 949 LBS.

OK
FP

23
244

to Les

TOTAL WGT. 3549#

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-908-D (D)	EWK 12/12/77
		DCG 12/14/77
	TYPED BY	
	prj 1/31/78	

MAKING NOTES

REMARKS

NAME: DROLOR® YELLOW- LIGHT — NON-BLEEDING

INSTRUCTIONS — -PRESSING- — RECORD

VAT	2,4A				
DATE	1-25-80	SAW			
TIME	6:05 pm				
RELEASED BY	AC				
PRESS	2	22	23	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION
WASH TO 2000 OHMS with 135-145°F water
TEST AFTER 2 HOURS
LOAD On 6 cars

DF

SAMPLES 8 oz Jar
DELIVER TO CIL for color

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	12 Noon				
CAKES USED	46				
WATER ON	5. PM				
HRS. WASHED	21 H 25				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	5				
NO. CARS LOADED					

EXPLAIN LOSSES

POSSIBLE CONTAMINATED WITH KY-781 Valve on Filling Side of #23 Pr. Perkins [redacted] while use #23 Pump to Filling #22 PR.

SAMPLED BY RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3647
RELEASED BY

-GRINDING-

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT Can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

DUP050094317

33941
124
41

3.33	+
0.14	-
3.35	+
0.14	-
3.21	+
0.14	-
3.48	+
0.14	-
3.20	+
0.14	-
3.20	+
0.14	-
3.35	+
0.14	-
3.21	+
0.14	-
3.32	+
0.14	-
3.27	+
0.14	-
3.22	+
0.14	-
2.01	+
0.14	-
36.47	*

DUP050094318