FILE NAME: Johns-Manville (JMA)

DATE: 1940 Dec 18

DOC#: JMA285

DOCUMENT DESCRIPTION: Monsanto Chemical Co., Specification Sheets - Asbestos Floats

MASTER COPY

TO BE RETAINED IN STANDARDS DEPT. FILES

Monsanto Chemical Company

PLASTICS DIVISION

RAW MATERIAL SPECIFICATION

SUPERSEDED

For ASBESTOS FLOATS Number 101-A

Superseding specification issued on 12/18/40 1 sheets Page 1

PROPERTIES:	SPECIFICATIONS:	TEST METHODS:
1. APPEARANCE:	Whitish Gray, Fiberous, Flocculent, Free Flowing.	Visual
2. MOISTURE: % by Wt.	1.0 Max.	Drying for 1 Hr. @ 110°C.
3. PARTICLE SIZE:		SDP #114-43-3
% Retained on 10 Mesh:	0.0 Max.	
% Retained on 20 Mesh:	0.5 Max.	
% Through 80 Mesh:	17.0 Max.	
4. GRIT - % BY WEIGHT:	1.0	SDP #114-84
5. WATER OF CRYSTALLIZATION: % By Weight	15.0	Heating small sample @ 1000°C. for 3 hrs.

REFERENCE: T.E. DALY 1/4/50 - Particle Size.

SUPERSEDED JAN 63

ISSUED JAN 18 1950
STANDARDS DEPARTMENT
By E. Brown

00012

STER COPY

TO BE RETAINED IN STANDARDS DEPT. FILES

Monsanto Chemical Company

PLASTICS DIVISION

DISTRIBUTION RESTRICTED

ADDITION OF ADDITIONAL NAMES MUST BE APPROVED THROUGH THE STANDARDS DEPT.

RAW MATERIAL SPECIFICATION

SUPERSEDED

For ASBESTOS FLOATS Number 101-A

Superseding specification issued on 12/18/40 1 sheets Page 1

PROPERTIES:	SPECIFICATIONS:	TEST METHODS:
1. APPEARANCE:	Whitish Gray, Fiberous, Flocculent, Free Flowing.	Visual
2. MOISTURE: % by Wt.	1.0 Max.	Drying for 1 Hr. @ 110°C.
3. PARTICLE SIZE:		SDP #114-43-3
% Retained on 10 Mesh:	0.0 Max.	
% Retained on 20 Mesh:	0.5 Max.	
% Through 80 Mesh:	17.0 Max.	
4. GRIT - % BY WEIGHT:	1.0	SDP #114-84
5. WATER OF CRYSTALLIZATION: % By Weight	15.0	Heating small sample @ 1000°C. for 3 hrs.

CANCELLED JAN 83

ISSUED JAN 18 1950
STANDARDS DEPARTMENT
By E. Brown

00014