

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE K-788 LOT 34978

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>50</u>	<u>64</u>	<u>31350</u>		

STUMP

TOTAL NET WT. 31350 PKG. N-CODE 1130

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

RT 312450

CG 03 CODE KY-788-D PKG.
→ MAR 17 34978
EST. WGT. 960 860 LBS.

OK
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

23
240

PROCESSES KY-788-D (J)	APPROVED BY EWK 9/22/76
	DCG 9/27/76
TYPED BY NE 2/17/77	
MAKING NOTES	

REMARKS

3460
Total Wgt. 3560# Req()

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3/21/80					STARTED	5:30 PM	1:10			
TIME	5:30					CAKES USED	54				
RELEASED BY	58					WATER ON	6A	1:30			
PRESS	22	23	24			HRS. WASHED	6	25 HRS			
NO. OF CAKES	46	46	46			OHMS	2000	2000			
PRESS WITH						HRS. WASHED					
WASH TO 2000						OHMS					
TEST AFTER 2						HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	17	5			
						EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR
DELIVER TO CIL for Color

SAMPLED BY 1708 RELEASED BY 120

-DRYING-

Dry 12 hrs at 220 °F L.V. H.V.
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

No Drums 14
LUMP WGT. 3360
RELEASED BY 120

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

DATE MIXED

SAMPLES 1 Env. & 1 Pt can

DELIVER TO C T L

SAMPLED BY

RELEASED BY

3 4 9.7 8 #
.41 #
3.24 #
.00 T

2.63
.14 -
2.55
.14 -
2.53
.14 -
2.44
.14 -
2.58
.14 -
2.53
.14 -
2.42
.14 -
2.52
.14 -
2.53
.14 -
2.42
.14 -
2.47
.14 -
2.63
.14 -
2.53
.14 -
2.78
.14 -
3 3.60 T