

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 14787 LOT 34595

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>61</u>	<u>3050</u>		

STUMP

TOTAL NET WT. 3050 PKG. N-CODE 1135

PROD. SPVR. DATE WHSE. OPER.

2PP 313180

N 26319

23
240

CG 03 CODE KY-787-D PKG. _____
→ FEB 27 34595
EST. WGT. 1090 990 LBS.

OK
FP

Suspect quality
Wash Prior after dropping -

Total Wgt. 3490# 3390

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	
MAKING NOTES	

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		2-28-80			STARTED	4 AM				
TIME		1255 AM			CAKES USED	46				
RELEASED BY		83			WATER ON	10 PM				
PRESS	22	23	24	24	HRS. WASHED	8				
NO. OF CAKES	46	46	46	52	OHMS	2500				
PRESS with					HRS. WASHED					
WASH TO 2000					OHMS					
TEST AFTER 2					HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO c1 for color

SAMPLED BY RELEASED BY AC.

-DRYING-

Dry 12 hrs at 220°F
Then Dry 8 hrs at 160°F

LUMP: -- OK -- WET -- SALTS -- CONTAMINATED

See above note

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3149
RELEASED BY

-GRINDING-

MILL 039 HSP 3/32" RD SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV 8 1 Pt. can
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093830

N 26319.01

34612

41

446

0.00 *
2.48 +
0.14 -
2.44 +
0.14 -
2.52 +
0.14 -
2.58 +
0.14 -
2.45 +
0.14 -
2.69 +
0.14 -
2.55 +
0.14 -
2.42 +
0.14 -
2.45 +
0.14 -
2.47 +
0.14 -
2.59 +
0.14 -
2.42 +
0.14 -
2.38 +
0.14 -
1.24 +
0.14 -
31.72 *