

TRADE NAME: Ankorkote
 CLASS: Enamel Undercoaters
 COLOR: White
 CODE NO: 3927
 QUALITY: Second

	LBS	YIELD(GAL)	UNIT COST	TOTAL COST
<u>PIGMENT: 60 %</u>				
Calcium Linoleate	30	3.75	.098 lb	2.94
" Carbonate	200	9.24	.0163 "	3.26
Diatomaceous Silica	50	2.83	.036 "	1.80
Rutile Titanium Calcium	150	5.81	.0606 "	9.09
Titanated Lithopone	300	8.46	.059 "	17.70
Zinc Oxide	25	.53	.078 "	1.95
<u>VEHICLE: 40 %</u>				
Bodied Non-Penetrating Oil	60	7.50	1.15 gal	8.63
Processed Linseed Oil	47.76	6.00	1.01 "	6.06
Mineral Spirits	195.60	30.00	.092 "	2.76
Drier	35.	5.00	.35 "	1.75
Varnish	170.25	22.50	.703 "	15.82
CALCULATED YIELD	1263.61	101.62		71.76
MANUFACT. LOSS 3 %		3.05		
ACTUAL YIELD		98.57		

COST ANALYSIS: indicate gal. or lb.

MATERIAL COST: per gal. or lb.

DIRECT LABOR

FACTORY OVERHEAD

BULK COST

COMPLETE PACKAGING COST (container plus filling)

FACTORY COST IN PACKAGE gal. or pound

HIGHEST PRICE IN MARCH 1942

(A) TO A COMPANY OWNED OR CONTROLLED OUTLET

(B) TO AN INDEPENDENT WHOLESALER

(C) BY COMPANY OWNED OR CONTROLLED OUTLET TO RETAIL CUSTOMER

(D) TO AN INDEPENDENT RETAILER (DEALER)

(E) TO OTHER (SPECIFY)

Gal .73
 .035
 .109
 .874
 .25
 1.124

1.339

1.571