MD-3-A

PACKAGE TICKET

CODE LJE-735 LOT E2K80

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
	2060	1	I	253
	1960	1	1	268

STUMP

TOTAL NET WT. 4020

LUMP WT. 3966 PKG. N-CODE

PROD. SUPV. [signature] DATE 7/11 OPERATOR

N37600

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YE-735-D PKG ____

PROCESSES APPROVED BY
YE-735-D (M) FWP 10/07/81
ALTERNATE
TYPED BY JMH

LOT F2K80 JUN 1 8 1982

EST. WT. 3819* LBS. 91/242 01 1P

MAKING NOTES _____

JOB NAME: 01YE735DPM ,

= PRESSING =

INSTRUCTIONS					RECORD					
VAT	242				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-23				STARTED	11:30AM				
TIME	2:15 PM				CAKES USED	50				
RELEASED BY	WM				WATER ON					
PRESS	2	91			HRS. WASHED	20				
NO.OF CAKES	32	42			M MHOS	160				
PRESS WITH AGITATION SEE BELOW					HRS. WASHED					
WASH TO 285 M MHOS WITH 35-75*F WATER.					M MHOS					
					HRS. WASHED					
TEST AFTER 2 HOURS.					M MHOS					
LOAD ON 5 CARS.					CAKE CONDITION					
STOP AGITATOR AT ABOUT 50*					NO CARS LOADED	5				
DO NOT EXTRUDE.					EXPLAIN LOSSES					

SAMPLES JAR
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 14 HRS AT 240*F MAY 1 - AUG. 31.
DRY 12 HRS AT 240*F SEPT. 1 - APR 30

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 12
LUMP WGT 3966

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY 2PP

= GRINDING =

'MIKROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW.

MAGNEHELIC READING ON ATOMIZER PANEL BOARD_____(1.0")_____

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 2 PT. CANS
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

N37600.01

DUP050045918

YE-735-D
F2K80

5 con.

12 drums

80	#
41	#
348	#
0	T
371	+
12	−
355	+
12	−
344	+
12	−
363	+
12	−
341	+
12	−
347	+
12	−
347	+
12	−
351	+
12	−
345	+
12	−
336	+
12	−
342	+
12	−
268	+
12	−
3966	T