

NOTICE: If the film image
is less clear than this
notice, it is due to the
quality of the document
being filmed

54

"Dutch Boy"
TEMEX 3

*The most effective stabilizer
for vinyl-asbestos flooring*



DUTCH BOY CHEMICALS

A Product Development of
NATIONAL LEAD COMPANY

2-68-51

00053

0532

NLI 11609

"Dutch Boy" TEMEX 3

"DUTCH BOY" TEMEX 3 is a new barium-silic organic stabilizer with a special combination of properties for vinyl- asbestos tiles.

1. Superb heat stability
2. Tile colors retained at initial shades
3. Complete freedom from outside staining
4. Very good light stability
5. Adds no lubricity to stock

The heat stabilizing action of TEMEX 3 carries asbestos-filled flooring stock easily through the strenuous milling, calendaring and closed mold heat treatment cycles normally encountered in production. Comprehensive oven, milling, and molding tests show a retention of initial color beyond any point previously obtained. Color deterioration, such as pinking and bluing, which are associated with unfavorable interactions between stabilizer and impurities in asbestos fillers are eliminated by TEMEX 3.

TEMEX 3 provides complete freedom from staining when the flooring product is used in contact with oilier compounds of any type.

The light stability of TEMEX 3 is sufficient to protect a vinyl-asbestos tile throughout considerable exposure to direct sunlight. Since vinyl-asbestos flooring is usually installed indoors, it receives only indirect and intermittent exposure. Consequently, TEMEX 3 gives a very substantial reserve against spotting or discoloration.

An important advantage of TEMEX 3 is its complete freedom from any tendency to lubricate in vinyl flooring stocks. This makes it possible to use any desired level of stabilizer without affecting the processing characteristics through calendaring and molding operations.

00053

NLI 116099

0573

54

With its combination of high heat stability and non-lubricating action, TEMEX 3 is particularly suitable for tile stocks where the maintenance of critical color values is extremely important, such as patch and whites.

Recommendation

The quantity of TEMEX 3 recommended for a floor tile depends upon the amount and type of asbestos filler used in the formulation. This may range from 4% to 10% TEMEX 3 (resin basis) for various types of tile. For example, about 5% to 6% (resin basis) gives optimum stability in conventional tiles containing approximately equal weights of asbestos filler and resin.

Typical Properties

Composition	Barium-Zinc Oxide
Form and Color	Fine White Powder
Specific Gravity	2.15
Fineness, retained on 100 mesh sieve, %	0.01

2-68-87

00053

0534

NLI 116100