

Measurements (cont'd)

Width, length, gaps between lining & shoe showed no significant difference on any of the six pcs.

- Linings were then removed from shoes and $\frac{1}{2}$ of each lining sent to Mr. A.B. Indelicato at Abex Corp on 5-30-79 (Rec'd 6-4-79).

Date codes on back of linings were recorded (Date stamped by Abex during processing):

1P - 9018	(Jan 18, 1979)
1S - 9085	(Mar 26, '79)
2P - 9022	(Jan 22, '79)
2S - 9073	(Mar 14, '79)
3P - 6099	(Apr. 9, 1976)
3S - 6262	(Sept 19, '76)

- Gogan hardness of the six pcs ranged from GC 20-25 which is considered very close and well within spec of 15-41 on Pri & 17-36 on Sec.

Following tests will be completed this week:

- SAE J-661 Friction Machine Tests
- Specific Gravity, Acetone Extraction, Ash Content, Infra Red trace.

B. L. Huse
6-4-79